

Specification for

Steel wire for general fencing purposes

ICS 77.140.65

Committees responsible for this British Standard

The preparation of this British Standard was entrusted to Technical Committee ISE/26, Steel wire, upon which the following bodies were represented:

- Bicycle Association of GB
- British Cable Makers Confederation
- British Rubber Manufacturers Association Ltd.
- British Stainless Steel Association
- Electricity Association
- Federation of Wire Rope Manufacturers of Great Britain
- Forestry Commission
- Health and Safety Executive
- Institute of Spring Technology
- National Centre of Tribology
- Society of Chain Link Fencing Manufacturers
- Society of Motor Manufacturers and Traders Limited
- Stainless Steel Wire Industry Association
- UK Steel Association
- Welding Manufacturers Association (BEAMA Ltd.)
- Woven Wire Association

This British Standard, having been prepared under the direction of the Engineering Sector Board, was published under the authority of the Standards Board and comes into effect on
15 June 1998

© BSI 1998

The following BSI references relate to the work on this standard:
Committee reference ISE/26

ISBN 0 580 29537 0

Amendments issued since publication

Amd. No.	Date	Text affected

Contents

	Page
Committees responsible	Inside front cover
Foreword	ii
1 Scope	1
2 Normative references	1
3 Materials	1
4 Wire diameter and tolerances	1
5 Coatings	1
6 Tensile strength	1
7 Inspection and testing	2
8 Marking	2
Table 1 — Nominal diameters of wires for general fencing purposes	1
Table 2 — Minimum tensile strength for drawn carbon steel line wire	2

Foreword

This British Standard has been prepared by Technical Committee ISE/26. It supersedes BS 4102:1990 which is withdrawn. This new edition of BS 4102 has been editorially amended to remove technical requirements which have been superseded by European Standards. It does not constitute a full revision of the standard.

This new edition of BS 4102 does not specify requirements for:

- wire for chain linking fence;
- barbed wire;
- wire and woven wire mesh for hinged joint fencing; and
- welded steel wire mesh.

Requirements for these wires have been included in BS EN 10223-1, -4, -5 and -6, published simultaneously with this British Standard.

A British Standard does not purport to include all necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 and 2, an inside back cover and a back cover.

1 Scope

This British Standard specifies requirements for zinc coated steel wire, used in the construction of fences, including those conforming to BS 1722 for the following applications:

- a) wire for cleft chestnut pale fencing;
- b) general purpose line wire;
- c) general purpose stirrup wire;
- d) general purpose tying wire;
- e) organic coated wire for strained wire dropper fencing.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this British Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. For undated references, the latest edition of the publication referred to applies.

BS EN 10218-1, *Steel wire and wire products — General — Part 1: Test methods*.

BS EN 10218-2, *Steel wire and wire products — General — Part 2: Wire dimensions and tolerances*.

BS EN 10244-1, *Non-ferrous metallic coating for steel wire — Part 1: General principles*.

BS EN 10244-2, *Non-ferrous metallic coating for steel wire — Part 2: Zinc and zinc alloy coatings*.

BS 1722-3, *Fences — Part 3: Specification for strained wire fences*.

3 Materials

3.1 The wire shall be as uniform as possible and free from internal and surface defects that could adversely affect its performance. Wire in coil shall be “dead cast” to lie in uniform circles with no significant helical lift.

NOTE Where wire has been zinc coated by the hot dip method, thick coatings may not be entirely free from surface irregularities and, provided these are within the generally accepted limits of good practice, they should not be cause for rejection of the wire.

3.2 With the exception of the line wires covered in **3.3**, the wire shall be of low carbon steel in the softened condition with tensile properties in accordance with **6.1**.

3.3 Line wires described as “high tensile” or “spring steel” shall be of drawn carbon steel having tensile properties in accordance with **6.3**.

4 Wire diameters and tolerances

4.1 Diameter

The nominal diameters of wires shall be in accordance with Table 1.

NOTE The approximate lengths are for information and have been calculated assuming a density of 7.82 kg/dm³ for zinc coated wire.

4.2 Tolerances on diameter

The tolerances on diameter shall be in accordance with EN 10218-2 T1.

5 Coatings

The wire shall be zinc coated in accordance with BS EN 10244-1 and -2.

When required (see section 4 of BS 1722-3:1986) 3.15 mm zinc coated high tensile wire shall be organic coated. The overall nominal diameter shall be 4.00 mm and the concentricity of the organic coating shall be $\pm 20\%$ of the nominal radial thickness.

6 Tensile strength

6.1 When tested in accordance with BS EN 10218-1, the tensile strength shall be in accordance with **6.2** or **6.3**.

6.2 For wire in the softened condition the tensile strength shall be within the range 350 N/mm² to 550 N/mm².

6.3 For drawn carbon steel line wire the tensile strength shall be not less than the values given in Table 2.

Table 1 — Nominal diameters of wires for general fencing purposes

Nominal wire diameter mm	Approximate length per 100 kg m	Nominal wire diameter mm	Approximate length per 100 kg m
1.60	6359	3.00	1809
1.90	4510	3.15	1641
2.00	4070	3.55	1292
2.24	3245	4.00	1018
2.50	265	4.50	804
2.65	2318	5.00	651

Table 2 — Minimum tensile strength for drawn carbon steel line wire

Nominal wire diameter mm	Usual description N/mm ²	Minimum tensile strength
2.50	High tensile	1050
2.65	Spring steel	1400
3.15	High tensile	1050
3.15	Spring steel	1400

7 Inspection and testing

Test lengths sufficient for all the appropriate tests shall be selected from wire coiled at a frequency of one from the product of one original rod coil or from each 1 t.

The tensile strength shall be determined in accordance with BS EN 10218-1 and shall be calculated using the nominal overall diameter for zinc coated wire and the nominal core wire diameter for organic coated wire.

8 Marking

Each coil of wire shall be securely bound and have attached a durable label bearing the following information:

- a) the manufacturer’s name or identification;
- b) the number and date of this British Standard¹⁾, i.e. BS 4102:1998;
- c) the nominal wire diameter;
- d) and in addition, for high tensile wire, the specified tensile strength.

The starting end of the coil of wire shall be identified.

¹⁾ Marking BS 4102:1998 on or in relation to a product represents a manufacturer’s declaration of conformity, i.e. a claim by or on behalf of the manufacturer that the product meets the requirements of the standard. The accuracy of the claim is therefore solely the responsibility of the person making the claim. Such a declaration is not to be confused with third party certification of conformity.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.