

Grain-oriented electrical steel sheet and strip delivered in the fully processed state

The European Standard EN 10107:2005 has the status of a
British Standard

ICS 77.140.50

National foreword

This British Standard is the official English language version of EN 10107:2005. It supersedes BS EN 10107:1996 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/NFE/5, Magnetic alloys and steel, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 15 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 17 February 2006

© BSI 17 February 2006

ISBN 0 580 46951 4

Amendments issued since publication

Amd. No.	Date	Comments

English Version

Grain-oriented electrical steel sheet and strip delivered in the fully processed state

Tôles et bandes magnétiques en acier à grains orientés
livrées à l'état fini

Kornorientiertes Elektroblech und -band im
schlussgeglühten Zustand

This European Standard was approved by CEN on 27 June 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Classification and designation.....	5
5 Information to be supplied by the purchaser	6
6 General requirements.....	6
7 Technical requirements	7
8 Inspection and testing.....	11
9 Marking, labelling and packaging	14
10 Complaints	14
Annex A (informative) Maximum specific total loss at 60 Hz.....	15

Foreword

This European Standard (EN 10107:2005) has been prepared by Technical Committee ECISS/TC 24 “Electrical steel sheet and strip qualities - Qualities, dimensions, tolerances and specific tests”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2006, and conflicting national standards shall be withdrawn at the latest by February 2006.

This document supersedes EN 10107:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies the steel grades of grain-oriented electrical sheet and strip in nominal thicknesses of 0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm; in particular, general requirements, magnetic properties, geometric characteristics and tolerances and technological characteristics, as well as inspection procedures.

This European Standard applies to Goss textured grain-oriented magnetic sheet steel supplied in the final annealed condition in sheets or coils, and intended for the construction of magnetic circuits.

The materials are grouped into two classes :

- a) conventional grain oriented material ;
- b) high permeability grain oriented material .

They correspond to Clause C22 of IEC 60404-1:2000.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10021, *General technical delivery requirements for steel and iron products*

EN 10027-1, *Designation systems for steel - Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10204, *Metallic products — Types of inspection documents*

EN 10251, *Magnetic materials - Methods of determination of the geometrical characteristics of electrical steel sheet and strip*

EN 10280, *Magnetic materials — Methods of measurement of the magnetic properties of electrical sheet and strip by means of a single sheet tester*

EN 10282:2001, *Magnetic materials — Method of test for the determination of surface insulation resistance of electrical sheet and strip*

EN 60404-2, *Magnetic materials — Part 2: Methods of measurement of the magnetic properties of electrical steel sheet and strip by means of an Epstein frame (IEC 60404-2:1996)*

EN ISO 7799, *Metallic materials — Sheet and strip 3 mm thick or less — Reverse bend test (ISO 7799:1985)*

IEC 60050-121:1998, *International Electrotechnical Vocabulary — Chapter 121: Electromagnetism*

IEC 60050-221:1990, *International Electrotechnical Vocabulary — Chapter 221: Magnetic materials and components*

IEC 60404-1:2000, *Magnetic materials — Part 1: Classification*

IEC 60404-13, *Magnetic materials — Part 13: Methods of measurement of density, resistivity and stacking factor of electrical steel sheet and strip*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions of the principal terms relative to magnetic properties given in IEC 60050-121:1998 and IEC 60050-221:1990 and the following apply.

3.1

edge camber

greatest distance between a longitudinal edge of the sheet and the line joining the two extremities of the measured length of this edge

3.2

flatness

property of a sheet or of a length of strip which is characterized by the wave factor i.e. by the relation of the height of the wave to its length

3.3

number of bends

number of alternate bends possible before the appearance of the first crack in the base metal visible to the naked eye indicating the ductility of the material

3.4

internal stresses

stresses which are characterized by a deviation in relation to the line of cutting

4 Classification and designation

4.1 Classification

The steel grades covered by this European Standard are classified according to the value of maximum specific total loss in watts per kilogram and according to the nominal thickness of the material (0,23 mm, 0,27 mm, 0,30 mm, 0,35 mm).

4.2 Designation

4.2.1 For the steel grades covered by this European Standard, the steel names are allocated in accordance with EN 10027-1. The steel numbers are allocated in accordance with EN 10027-2.

4.2.2 The steel names comprise the following in the order given :

- a) capital letter M for electrical steel,
- b) a number of one hundred times the specified value of maximum specific total loss at 50 Hz, in watts per kilogram corresponding to the nominal product thickness, at 1,7 T,
- c) one hundred times the nominal thickness of the product, in millimetres,
- d) the characteristic letter :
 - S for conventional grain oriented products ;
 - P for high permeability grain oriented products.

EXAMPLE Conventional grain oriented electrical steel sheet or strip with a maximum specific total loss at 1,7 T of 1,50 W/kg at 50 Hz and a nominal thickness of 0,30 mm, supplied in the fully processed state:

M150-30S

5 Information to be supplied by the purchaser

5.1 Mandatory information

For material to comply adequately with the requirements of this standard, the purchaser shall include the following information in his enquiry or order :

- a) quantity,
- b) type of product (strip or sheet),
- c) number of this European Standard (EN 10107),
- d) steel name or number (see 4.2.1),
- e) dimensions of sheets or strips required (including any limitations on the external diameter of a coil) (see 6.2 and 7.2.2),
- f) limitations on the mass of a bundle of sheets or of a coil (see 6.2),
- g) residual curvature for coils (see 7.2.6),
- h) minimum insulation coating resistance (see 7.3.5),
- i) inspection procedure required including the nature of the related documents (see 8.1).

5.2 Options

A number of options are specified in this standard and listed below. If the purchaser does not indicate his wish to implement one of these options, the products shall be supplied in accordance with the basis specification of this standard (see 5.1).

- a) permissibility of welds and its marking (see 6.2);
- b) compatibility between fluid and coating (see 6.4, NOTE);
- c) plus tolerances for nominal width (see Table 3, footnote a);
- d) requirement concerning residual curvature (see 7.2.6);
- e) acceptance unit other than 3 t (see 8.1);
- f) test temperature other than $(23 \pm 5) ^\circ\text{C}$ (see 8.4.1);
- g) alternative method for determination of magnetic properties (see 8.4.2, NOTE);
- h) marking of the products (see Clause 9).

6 General requirements

6.1 Production process

The production process of the steel and its chemical composition are left to the discretion of the manufacturer.

6.2 Form of supply

The material is supplied in bundles in the case of sheets and in coils in the case of strip.

The mass of bundles of sheets or of coils shall be agreed at the time of enquiry and order.

The recommended value for the internal diameter of coils is approximately 508 mm.

Sheets which make up each bundle shall be stacked so that the side faces are substantially flat and approximately perpendicular to the top face.

Strip shall be of constant width and wound in such a manner that the edges are superimposed in a regular manner and that the side faces of the coil are substantially flat.

Coils shall be sufficiently tightly wound so that they do not collapse under their own weight.

Strip may exhibit welds resulting from the removal of defective zones if agreed at the time of enquiry and order. If necessary the marking of welds may be agreed at the time of enquiry and order.

For coils containing welds, each part of the strip shall be of the same grade.

The edges of parts welded together shall not be so much out of alignment as to affect the further processing of the material.

6.3 Delivery condition

Grain-oriented products are usually supplied with an insulating coating on both sides. This coating generally consists of a so called glass film composed essentially of silicates of magnesium on which has been deposited a second coating of inorganic constituents such as phosphates, normally as part of a thermal flattening operation ¹⁾.

6.4 Surface condition

The surfaces shall be smooth and clean, free from grease and rust ²⁾. Dispersed defects such as scratches, blisters, cracks, etc., are permitted if they are within the limits of the tolerances on thickness and if they are not detrimental to the correct use of the supplied material.

The insulation coating present on the surface of the material shall be sufficiently adherent so that it does not become detached during cutting operations or heat treatment under conditions specified by the supplier.

NOTE If the product is to be immersed in a fluid, an agreement, initiated by the purchaser, should be reached to ensure compatibility between the fluid and the coating.

6.5 Suitability for cutting

The material shall be able to be cut at any point and into the usual shapes thus ensuring accurate working with the correct cutting tools.

7 Technical requirements

7.1 Magnetic properties

7.1.1 General

The properties defined in 7.1.2 and 7.1.3 are applicable to materials in the delivery conditions defined in 6.3.

7.1.2 Magnetic polarization

1) Other types of coating exist which are used only when particularly specified.

2) Not to be confused with some colouration of the insulating coating inherent in the manufacturing process.

The specified minimum values of the magnetic polarization for a magnetic field strength of 800 A/m (peak value) shall be as given in Tables 1 and 2.

The magnetic polarization shall be determined in an alternating magnetic field (expressed as a peak value) at 50 Hz.

Table 1 — Technological and magnetic properties of conventional products

Steel grade		Nominal thickness mm	Maximum specific total loss at 50 Hz and 1,5 T 1,7 T W/kg		Minimum magnetic polarization for H = 800 A/m ^a T	Minimum stacking factor
Steel name	Steel number					
M110-23S	1.0863	0,23	0,73	1,10	1,78	0,945
M120-23S	1.0864	0,23	0,77	1,20	1,78	0,945
M127-23S	1.0860	0,23	0,80	1,27	1,75	0,945
M120-27S	1.0868	0,27	0,80	1,20	1,78	0,950
M130-27S	1.0866	0,27	0,85	1,30	1,78	0,950
M140-27S	1.0865	0,27	0,89	1,40	1,75	0,950
M130-30S	1.0859	0,30	0,85	1,30	1,78	0,955
M140-30S	1.0862	0,30	0,92	1,40	1,78	0,955
M150-30S	1.0861	0,30	0,97	1,50	1,75	0,955
M140-35S	1.0858	0,35	1,00	1,40	1,78	0,960
M150-35S	1.0857	0,35	1,05	1,50	1,78	0,960
M165-35S	1.0856	0,35	1,11	1,65	1,75	0,960

^a It has been common practice for many years to give values of magnetic flux density. In fact the Epstein frame is used to determine magnetic polarization (intrinsic flux density) which is defined as:

$$J = B - \mu_0 H$$

where;

- J is the magnetic polarization
- B is the magnetic flux density
- μ_0 is the magnetic constant: $4 \pi 10^{-7} \text{ H m}^{-1}$
- H is the magnetic field strength.

NOTE The difference between B and J at 800 A/m amounts up to 0,001 T.

7.1.3 Specific total loss

The specified values of maximum specific total loss at 50 Hz shall be as given in Tables 1 and 2. They apply to aged test specimens cut parallel to the axis of rolling.

In the case of Epstein strips, they shall receive, after cutting, a stress relief heat treatment under conditions left to the discretion of the manufacturer.

NOTE A stress relief heat treatment is not normally applied to single sheet test specimens.

Annex A gives, for guidance, the maximum specific total loss at 60 Hz for a magnetic polarization of 1,7 T.

Table 2 — Technological and magnetic properties of high permeability products

Steel grade		Nominal thickness mm	Maximum specific total loss at 50 Hz and 1,7 T W/kg	Minimum magnetic polarization for $H = 800 \text{ A/m}^a$ T	Minimum stacking factor
Steel name	Steel number				
M85-23P ^b	1.0822	0,23	0,85	1,88	0,945
M90-23P ^b	1.0835	0,23	0,90	1,88	0,945
M95-23P	1.0836	0,23	0,95	1,88	0,945
M100-23P	1.0879	0,23	1,00	1,85	0,945
M90-27P ^b	1.0838	0,27	0,90	1,88	0,950
M95-27P ^b	1.0839	0,27	0,95	1,88	0,950
M103-27P	1.0880	0,27	1,03	1,88	0,950
M100-30P ^b	1.0852	0,30	1,00	1,88	0,955
M105-30P	1.0886	0,30	1,05	1,88	0,955
M111-30P	1.0881	0,30	1,11	1,88	0,955
M125-35P	1.0854	0,35	1,25	1,88	0,960
<p>^a It has been common practice for many years to give values of magnetic flux density. In fact the Epstein frame is used to determine magnetic polarization (intrinsic flux density) which is defined as :</p> $J = B - \mu_0 H$ <p>where;</p> <p>J magnetic polarization B magnetic flux density μ_0 magnetic constant: $4 \pi 10^{-7} \text{ H m}^{-1}$ H magnetic field strength</p> <p>NOTE The difference between B and J at 800 A/m amounts up to 0,001 T.</p> <p>^b This grade may be delivered in the domain refined condition.</p>					

7.2 Geometric characteristics and tolerances

7.2.1 Thickness

The nominal thicknesses of the material are 0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm.

For thickness tolerance, a distinction is made between:

- the allowable tolerance on the nominal thickness within the same acceptance unit,
- the difference in thickness in a sheet or in a length of strip in a direction parallel to the direction of rolling,
- the difference in thickness in a direction perpendicular to the direction of rolling. This tolerance applies only to materials with a width greater than 150 mm.

At any point, the allowable tolerance on the nominal thickness within the same acceptance unit shall not exceed $\pm 0,030 \text{ mm}$ except for the 0,23 mm thickness for which this tolerance shall not exceed $\pm 0,025 \text{ mm}$. The additional thickness due to welds with respect to the measured thickness of the steel sheet or strip shall not exceed 0,050 mm.

The difference in thickness in a sheet or in a length of strip of 1,5 m in a direction parallel to the direction of rolling shall not exceed 0,030 mm.

In addition, for material with a width greater than 100 mm, the difference in thickness in a direction perpendicular to the direction of rolling shall not exceed 0,020 mm, the measurements being made at least 40 mm from the edges.

7.2.2 Width

The available nominal widths are $\leq 1\,000$ mm.

The material can be supplied either in a width chosen from the specific range of the manufacturer, or in the finally used width.

Width tolerances:

- for material supplied in a width chosen from the specific range of the manufacturer, the tolerances permitted shall be $\begin{pmatrix} +2 \\ 0 \end{pmatrix}$ mm,
- for material supplied in the finally used width, the tolerances of Table 3 shall apply.

Table 3 — Tolerances on nominal width

Nominal width l (mm)	Tolerance ^a (mm)
$l \leq 150$	0 - 0,2
$150 < l \leq 400$	0 - 0,3
$400 < l \leq 750$	0 - 0,5
$l > 750$	0 - 0,6
^a If so agreed at the time of enquiry and order, the tolerances on the nominal width shall be plus tolerances.	

7.2.3 Length

The tolerances on length of sheets in relation to the length ordered shall be $\begin{pmatrix} +0,5 \\ 0 \end{pmatrix}$ %, but with a maximum of + 6 mm.

7.2.4 Edge camber

The verification of edge camber does not apply to material of width ≤ 150 mm. The edge camber shall not exceed 0,5 mm for a measuring length of 1,5 m.

7.2.5 Flatness (wave factor)

The verification of the flatness does not apply to material of width less than or equal to 150 mm. The wave factor (see 8.4.3.4), expressed as a percentage, shall not exceed 1,5 %.

7.2.6 Residual curvature

A requirement concerning residual curvature may be specified by agreement when ordering, for material of width greater than 150 mm.

In this case the distance between the bottom edge of the test piece and the supporting plate shall not exceed 35 mm for sheets and shall be subject to agreement for coils.

7.2.7 Burr height

The determination of the burr height applies only to material delivered in the width it will finally be used. The measured burr height shall not exceed 0,025 mm.

7.3 Technological characteristics

7.3.1 Density

The density of the material is not specified.

The conventional value of density used to calculate the magnetic properties and the stacking factor shall be 7,65 kg/dm³.

7.3.2 Stacking factor

The minimum values shall be as specified in Tables 1 and 2.

7.3.3 Number of bends

The specified minimum number of bends is 1. This value applies to test specimens cut parallel to the direction of rolling.

7.3.4 Internal stresses

The material shall be, as far as possible, free from internal stresses.

The verification of internal stress is not applicable to material of width less than 500 mm (slit material). The measured gap shall not exceed 1 mm (see 8.3.3.3).

7.3.5 Insulation coating resistance

A minimum value of the insulation coating resistance measured before or after the possible application of a stress relief heat treatment shall be agreed at the time of enquiry and order. The stress relief heat treatment, when applied, shall be carried out under conditions specified by the manufacturer.

The insulation coating resistance expressed in Ωmm^2 represents the surface insulation resistance offered to the passage of current across the coating.

8 Inspection and testing

8.1 General

The materials specified by this European Standard can be ordered with non-specific or specific inspection in accordance with EN 10021. However, as a dispensation from EN 10021, in the case of an order without inspection, the manufacturer shall supply a certificate giving the specific total loss of the supplied material.

In the case of an order with specific inspection, the type of inspection document in accordance with EN 10204 shall be specified at the time of enquiry and order. In this case, the delivery is divided into acceptance units.

Each acceptance unit shall comprise 3,0 t or the remaining fraction thereof of the same grade and the same nominal thickness. Different acceptance units may be adopted by special agreement.

For coils of more than 3,0 t, each coil shall constitute an acceptance unit.

Except by special agreement the same rules apply to the inspection of internal stresses, suitability for cutting, surface insulation resistance and tolerances of shape and dimensions.

When the products are delivered in the form of slit coils, the test results applying to the parent unit of acceptance shall apply.

8.2 Sampling

Test samples shall be taken from each acceptance unit.

The first internal turn and last external turn of the coils shall be considered as wrapping and not as representative of the quality of the rest of the coil; the selection of samples shall be made from the first internal or external turns, excluding the wrapping turn and outside any welding zones.

In the case of sheets, the selection shall preferably be made from the upper part of the bundle.

By choosing a suitable order for the execution of the tests, the same sample shall serve to check the various properties.

8.3 Preparation of test specimens

8.3.1 Magnetic properties

For the measurement of magnetic polarization and specific total loss, the test specimen for the 25 cm Epstein frame in accordance with EN 60404-2 shall consist of a minimum of 24 Epstein strips having the following dimensions :

- a) length 280 mm to 310 mm, the lengths being equal within a tolerance of $\pm 0,5$ mm,
- b) width $30 \text{ mm} \pm 0,2 \text{ mm}$.

All the test strips shall be cut parallel to the direction of rolling. The permitted tolerance for the angle between the direction of rolling and the direction of cutting is $\pm 1^\circ$.

As far as possible, the selection of test strips shall be made uniformly across the width of the product. The test strips shall be carefully cut without deformation. Cutting or punching shall be carried out only with well sharpened tools.

Before the measurements, the test strips shall be subjected to a stress relief heat treatment in accordance with the manufacturer's specification.

In the case of measurements of specific total loss on aged test pieces, these shall be heated at $225^\circ\text{C} \pm 5^\circ\text{C}$ for a duration of 24 h and shall be cooled to ambient temperature.

8.3.2 Geometrical characteristics and tolerances

For the measurement of thickness, width, flatness and edge camber, the test specimen shall consist of a sheet or a length of strip of about 1,5 m.

For the measurement of the residual curvature, the test specimen shall consist of a sample of $(500^{+2,5}_0)$ mm in length and of width equal to the delivery width of the sheet or strip.

8.3.3 Technological characteristics

8.3.3.1 Stacking factor

The test specimen shall consist of a least 24 strips of the same size; in case of dispute the test shall be made with 100 strips. They shall have a width of at least 20 mm and a surface area of at least $5\,000 \text{ mm}^2$, their widths being equal within a tolerance of $\pm 0,1 \text{ mm}$ as well as their lengths. The test strips shall be carefully deburred before the test.

8.3.3.2 Number of bends

Five test specimens at least 20 mm wide shall be taken from outside the welding zones, parallel to the direction of rolling, with a view to making the bend perpendicular to the direction of rolling. The edge of the material shall not constitute one side of the test specimen.

The test specimens shall be carefully cut without deformation.

8.3.3.3 Internal stresses

The test specimen shall consist of a sheet or 1,5 m length of strip.

8.3.3.4 Insulation coating resistance

For products ≥ 600 mm width, four strips shall be selected over the whole width of the material. The width of each strip depends on the method to be used, e.g. 50 mm for the Franklin method.

For products less than 600 mm wide, the selection for inspection of insulation coating resistance, shall be agreed at the time of enquiry and order.

Before the measurements, depending on the agreement (see 7.3.5), the test specimen may need to be heat treated in accordance with the specification of the manufacturer.

8.4 Test methods

8.4.1 General

For each specified property one test shall be carried out per acceptance unit. Unless otherwise specified, the tests shall be made at a temperature of (23 ± 5) °C.

8.4.2 Magnetic properties

The test shall be made using a 25 cm Epstein frame in accordance with EN 60404-2.

In the case of some domain-refined material (see Table 2, footnote b), according to the instructions of the manufacturer, the test shall be made using the single sheet method of EN 10280.

NOTE As an alternative to the Epstein Method, the single sheet tester described in EN 10280 can be used by agreement between the manufacturer and purchaser. In this case, the specified values to be obtained with the single sheet tester should also be agreed.

8.4.3 Geometrical characteristics and tolerances

8.4.3.1 Thickness

The measurement of thickness shall be made at any point located more than 40 mm from the edges. For materials of a width less than 80 mm, the measurement of thickness shall be made along the longitudinal axis of the sheet. This measurement shall be made using a micrometer with a resolution of 0,001 mm.

8.4.3.2 Width

The width shall be measured perpendicular to the longitudinal axis of the product.

8.4.3.3 Edge camber

The edge camber shall be determined in accordance with EN 10251.

8.4.3.4 Flatness (wave factor)

The wave factor shall be determined in accordance with EN 10251.

8.4.3.5 Residual curvature

The residual curvature in the longitudinal direction of the strip shall be determined in accordance with EN 10251.

8.4.3.6 Burr height

The burr height shall be determined in accordance with EN 10251.

8.4.4 Technological characteristics

8.4.4.1 Stacking factor

The stacking factor shall be measured in accordance with IEC 60404-13.

8.4.4.2 Number of bends

The test consists of bending the test specimen through 90° alternately to each side of its initial position, following the method of bending defined by EN ISO 7799. The radius of bending chosen shall be 5 mm.

A bend of 90° from the initial position with return to the initial position counts as one bend.

The test shall be stopped on the appearance in the base metal of the first crack visible to the naked eye. The last bend shall not be counted.

8.4.4.3 Internal stresses

The internal stresses shall be determined in accordance with EN 10251.

8.4.4.4 Insulation coating resistance

The measurement of the surface insulation resistance is described in EN 10282.

NOTE Normally, Mode A of EN 10282:2001 is the preferred method.

8.5 Retests

When a test does not give the specified result, this test shall be repeated on double the number of test specimens from other sheets of the acceptance unit or on other strips from the coils. The delivery shall be considered to conform with the order if all results of additional tests are in accordance with the requirements of this standard.

After re-treatment, the manufacturer has the right to present again for test acceptance units which had not been found to comply with the order.

9 Marking, labelling and packaging

Marking, labelling and packaging of the products may be agreed at the time of enquiry and order.

10 Complaints

Internal or external defects shall justify a complaint only if they are clearly prejudicial to the method of working or the judicious use of the material.

The purchaser shall give to the manufacturer the opportunity of convincing himself of the fairness of the claim by presenting the material in dispute and evidence for the complaint.

In all cases, the terms and conditions of complaints shall be in accordance with EN 10021.

Annex A (informative)

Maximum specific total loss at 60 Hz

Table A.1 — Maximum specific total loss at 60 Hz and 1,7 T

Steel grade		Maximum specific total loss at 60 Hz and 1,7 T W/kg
Steel name	Steel number	
to Table 1		
M110-23S	1.0863	1,45
M120-23S	1.0864	1,58
M127-23S	1.0860	1,67
M120-27S	1.0868	1,58
M130-27S	1.0866	1,71
M140-27S	1.0865	1,84
M130-30S	1.0859	1,71
M140-30S	1.0862	1,84
M150-30S	1.0861	1,97
M140-35S	1.0858	1,84
M150-35S	1.0857	1,97
M165-35S	1.0856	2,17
to Table 2		
M85-23P	1.0822	1,12
M90-23P	1.0835	1,18
M95-23P	1.0836	1,25
M100-23P	1.0879	1,32
M90-27P	1.0838	1,18
M95-27P	1.0839	1,25
M103-27P	1.0880	1,36
M100-30P	1.0852	1,32
M105-30P	1.0886	1,38
M111-30P	1.0881	1,46
M125-35P	1.0854	1,65

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.