Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

BRITISH STANDARD

BS EN 10217-5:2002
Incorporating Amendment No. 1

Welded steel tubes for pressure purposes — Technical delivery conditions —

Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties

The European Standard EN 10217-5:2002, with the incorporation of amendment A1:2005, has the status of a British Standard

ICS 23.040.10; 77.140.75

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

BSI British Standards

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

National foreword

This British Standard is the official English language version of EN 10217-5:2002, including amendment A1:2005. Together with BS EN 10217-3:2002 it supersedes BS 3602-2:1991 which is withdrawn.

The start and finish of text introduced or altered by CEN amendment is indciated in the text by tags [A1] ⟨A1]. Tags indicating changes to CEN text carry the number of the CEN amendment. For example, text altered by CEN amendment A1 is indicated by [A1] ⟨A1].

The UK participation in its preparation was entrusted by Technical Committee ISE/73, Steels for pressure purposes, to Subcommittee ISE/73/1, Steel tubes for pressure purposes, which has the responsibility to:

— aid enquirers to understand the text;

— present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;

— monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 36, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 26 June 2002

© BSI 6 March 2006

ISBN 0 580 39845 5

Amendments issued since publication

Amd. No.	Date	Comments
15470	6 March 2006	See national foreword

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN 10217-5

May 2002

+ A1

January 2005

ICS 23.040.10; 77.140.75

English version

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties
(includes amendment A1:2005)

Tubes soudés en acier pour service sous pression - Conditions techniques de livraison - Partie 5: Tubes soudés à l'arc immergé sous flux en poudre en acier non allié et allié avec caractéristiques spécifiées à haute température (inclut l'amendement A1:2005)

Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen - Teil 5: Unterpulvergeschweißte Rohre aus unlegierten und legierten Stählen mit festgelegten Eigenschaften bei erhöhten Temperaturen (enthält Änderung A1:2005)

This European Standard was approved by CEN on 25 April 2002. Amendment A1 was approved by CEN on 9 December 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2002 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Contents

Foreword 3
1 Scope 5
2 Normative references 5
3 Terms and definitions 6
4 Symbols 6
5 CLASSIFICATION AND DESIGNATION 7
5.1 Classification 7
5.2 Designation 7
6 Information to be supplied by the purchaser 7
6.1 Mandatory information 7
6.2 Options 8
6.3 Example of an order 8
7 Manufacturing process 8
7.1 Steelmaking process 8
7.2 Deoxidation process 8
7.3 Tube manufacture and delivery conditions 9
8 Requirements 10
8.1 General 10
8.2 Chemical composition 10
8.3 Mechanical properties 12
8.4 Appearance and internal soundness 14
8.5 Straightness 15
8.6 Preparation of ends 15
8.7 Dimensions, masses and tolerances 15
9 Inspection 18
9.1 Types of inspection 18
9.2 Inspection documents 19
9.3 Summary of inspection and testing 19
10 sampling 20
10.1 Frequency of tests 20
10.2 Preparation of samples and test pieces 21
11 Test methods 22
11.1 Chemical analysis 22
11.2 Tensile test on the base material 22
11.3 Traverse tensile test on the weld 23
11.4 Weld bend test 23
11.5 Impact test 23
11.6 Hydrostatic leak tightness test 24
11.7 Dimensional inspection 24
11.8 Visual examination 24
11.9 Non-Destructive Testing 24
11.10 Material identification 25
11.11 Retests, sorting and reprocessing 25
12 Marking 25
12.1 Marking to be applied 25
12.2 Additional marking 26
13 Protection 26
Annex A (normative) 27
Annex ZA (informative) 35
Bibliography 36

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Foreword

This document (EN 10217-5:2002) has been prepared by Technical Committee ECISS/TC 29, "Steel tubes and fittings for steel tubes", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2002, and conflicting national standards shall be withdrawn at the latest by November 2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

Other parts of EN 10217 are:

Part 1: Non-alloy steel tubes with specified room temperature properties.

Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties.

Part 3: Alloy fine grain steel tubes.

Part 4: Electric welded non-alloy steel tubes with specified low temperature properties.

Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties.

Part 7: Stainless steel tubes.

Another European Standard series covering tubes for pressure purposes is:

EN 10216: Seamless steel tubes for pressure purposes.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Foreword to amendment A1

This document (EN 10217-5:2002/A1:2005) has been prepared by Technical Committee ECISS/TC 29 "Steel tube and fittings for steel tubes", the secretariat of which is held by UNI.

This Amendment to the European Standard EN 10217-5:2004 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2005, and conflicting national standards shall be withdrawn at the latest by July 2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 97/23/EC.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

For relationship with EU Directive 97/23/EC, see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

1 Scope

This Part of EN 10217 specifies the technical delivery conditions in two test categories of submerged arc welded tubes of circular cross section, with specified elevated temperature properties, made of non-alloy and alloy steel.

2 Normative references

This European Standard incorporates by date or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For date references, subsequent amendments to or revisions of, any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

The requirements of this European Standard rule when they differ from those in the standards and documents referred to below:

EN 760, *Welding consumables - Fluxes for submerged arc welding – Classification*

EN 895, *Destructive tests on welds in metallic materials - Transverse tensile test.*

EN 910, *Destructive tests on weld in metallic materials -Bend test.*

EN 1321, *Destructive tests on welds in metallic materials - Macroscopic and microscopic examination of welds*

EN 10002-1, *Metallic materials - Tensile testing - Part 1 : Method of test (at ambient temperature.*

EN 10002-5, *Metallic materials - Tensile testing - Part 5 : Method of testing at elevated temperature*

EN 10020, *Definitions and classification of grades of steel.*

EN 10021, *General technical delivery requirements for steel and iron products.*

EN 10027-1, *Designation systems for steels - Part 1 : Steel names, principle symbols*

EN 10027-2, *Designation systems for steels - Part 2 : Numerical systems.*

EN 10045-1, *Metallic materials - Charpy impact test - Part 1 : Test method.*

EN 10052, *Vocabulary of heat treatment terms for ferrous products.*

EN 10204, *Metallic products - Types of inspection documents.*

ENV 10220, *Seamless and welded steel tubes - Dimensions and masses per unit length.*

EN 10246-9, *Non-Destructive Testing of steel tubes – Part 9: Automatic ultrasonic testing of the weld seam of submerged arc-welded steel tubes for the detection of longitudinal and/or transverse imperfections.*

EN 10246-10, *Non-Destructive Testing of steel tubes – Part.10: Radiographic testing of the weld seam of automatic fusion arc-welded steel tubes for the detection of imperfections.*

EN 10246-15, *Non-Destructive Testing of steel tubes - Part 15: Automatic ultrasonic testing of strip/ plate used in the manufacture of welded steel tubes for the detection of laminar imperfections.*

EN 10246-16, *Non-Destructive Testing of steel tubes - Part 16: Automatic ultrasonic testing of the area adjacent to the weld seam of welded steel tubes for the detection of laminar imperfections.*

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

EN 10246-17, *Non-Destructive Testing of steel tubes - Part 17: Ultrasonic testing of tube ends of seamless and welded steel tubes for the detection of laminar imperfections.*

EN 10256, *Non-Destructive Testing of steel tubes - Qualification and competence of level 1 and level 2 NDT personnel.*

prEN 10168 [1)], *Iron and steel products - Inspection documents - List of information and description*

prEN 10266 [1)], *Steel tubes, fittings and structural hollow sections - Symbols and definition of terms for use in product standards*

EN ISO 377, Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377:1997)

EN ISO 2566-1, *Steel - Conversion of elongation values – Part 1: Carbon and low-alloy steels (ISO 2566-1:1984)*

ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition*

CR 10260, *Designation systems for steel - Additional symbols*

CR 10261, *ECISS Information Circular IC 11 - Iron and steel - Review of available methods of chemical analysis.*

3 Terms and definitions

For the purposes of this Part of EN 10217 the terms and definitions given in EN 10020, EN 10021, EN 10052, prEN 10266 and the followings apply:

3.1
test Category
classification that indicates the extent and level of inspection and testing.

3.2
employer
organisation for which a person works on a regular basis.

NOTE The employer may be either the tube manufacturer or supplier or a third party organisation providing Non-Destructive Testing (NDT) services.

3.3
qualification of welding procedure
testing and inspection of the welding procedure in accordance with annex A by the manufacturer.

3.4
approval of welding procedure
testing and inspection of the welding procedure witnessed and approved in accordance with annex A by an authorised body.

4 Symbols

For the purposes of this part of EN 10217. The symbols given in prEN 10266 and the following apply:

---

1) In preparation; until this document is published as a European standard, a corresponding national standard should be agreed at the time of enquiry and order.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

— C1, C2 is the category conformity indicators (see 7.3.1 and 7.3.3.)

— TC test category.

5 CLASSIFICATION AND DESIGNATION

5.1 Classification

In accordance with the classification system in EN 10020, the steel grades P235GH and P265GH are classified as non-alloy quality steels and steel grade 16Mo3 is classified as an alloy special steel.

5.2 Designation

5.2.1 For the tubes covered by this Part of EN 10217 the steel designation consists of:

— the number of this Part of EN 10217;

plus either:

— the steel name in accordance with EN 10027-1 and CR 10260;

or:

— the steel number allocated in accordance with EN 10027-2.

5.2.2 The steel name of non alloy steel grades is designated by:

— the capital letter P for pressure purposes;

— the indication of the specified minimum yield strength at room temperature for thickness T less than or equal to 16 mm, expressed in MPa (see Table 4):

— the symbols GH for elevated temperature.

5.2.3 The steel name of alloy steel grade 16Mo3 is designated by the chemical composition (see Table 2).

6 Information to be supplied by the purchaser

6.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

a) the quantity (mass or total length or number);

b) the term "tube";

c) the dimensions (outside diameter D, wall thickness T) (see Table 6);

d) the designation of the steel grade in accordance with this Part of EN 10217 (see 5.2);

e) the test category for non-alloy steel (see 9.3).

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

6.2 Options

A number of options are specified in this Part of EN 10217 and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 6.1).

1) Tube manufacturing route (see 7.3.2).

2) Restriction on copper and tin content (see Table 2).

3) Product analysis (see 8.2.2).

4) Impact testing (see Table 4).

5) Longitudinal impact testing at -10°C for non-alloy steel (see Table 4).

6) Tensile testing at elevated temperature (see Table 5).

7) Special end preparation (see 8.6).

8) Exact lengths (see 8.7.3).

9) Type of inspection document other than the standard document (see 9.2.1).

10) Transverse weld tensile test (see Table 11).

11) Impact test in the weld area (see Table 11 and 10.2.2.5).

12) Test pressure for hydrostatic leak-tightness test (see 11.6).

13) Wall thickness measurement away from the ends (see 11.7).

14) Selection of Non-Destructive Testing method for the inspection of the weld seam (see 11.9.1).

15) Image quality class R1 of EN 10246-10 for the non-destructive radiographic inspection of the weld seam (see 11.9.1).

16) Additional marking (see 12.2).

17) Protection (see 13).

6.3 Example of an order

500 m of submerged arc welded tube with an outside diameter of 406,4 mm, a wall thickness of 4,5 mm in accordance with EN 10217-5, made of steel grade P265GH, test category 1, with a 3.1.C inspection certificate in accordance with EN 10204:

500 m – Tube – 406,4 x 4,5 – EN 10217-5 – P265GH – TC 1 – Option 9 : 3.1.C

7 Manufacturing process

7.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer.

7.2 Deoxidation process

Steels shall be fully killed.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

7.3 Tube manufacture and delivery conditions

7.3.1 All NDT activities shall be carried out by qualified and competent level 1,2 and/or 3 personnel authorised to operate by the employer.

The qualification shall be in accordance with EN 10256 or, at least, an equivalent to it.

It is recommended that the level 3 personnel be certified in accordance with EN 473 or, at least, an equivalent to it.

The operating authorisation issued by the employer shall be in accordance with a written procedure.

NDT operations shall be authorised by a level 3 NDT individual approved by the employer.

NOTE The definition of level 1,2 and 3 can be found in appropriate Standards, e.g. EN 473 and EN 10256.

For pressure equipment in categories III and IV (of Directive 97/23-EC) the personnel shall be approved by a recognised third-party organisation. Tubes not conforming to this requirement shall be marked “C 2”, unless a requirement to mark “C1” (see 7.3.3) applies

7.3.2 The tubes shall be manufactured by a submerged arc welding (SAW) process and in accordance with one of the routes as specified in Table 1.

Unless Option 1 is specified the manufacturing route is at the discretion of the manufacturer.

Option 1: *The manufacturing route is specified by the purchaser.*

Tubes shall be submerged arc welded using at least one weld run on the inside and one weld run on the outside of the tube.

The strip used for the manufacture of the helically submerged arc welded (SAWH) tubes shall have a width of not less than 0.8 times or more than 3.0 times the outside diameter of the tube.

The finished tubes shall not include welds used for joining together lengths of the hot or cold rolled strip or plate prior to forming except that for helically welded.

For helycally welded submerged arc welded (SAWH) tubes, when the weld joining lengths of strip are part of the delivered tube, they shall have the welding procedure qualified in accordance with annex A and the weld shall be subjected to the same inspection and testing as the helical weld.

7.3.3 Welding shall be carried out by suitably qualified personnel in accordance with suitable operating procedures.

For pressure equipment in categories II, III, and IV, (of Directive 97/23-EC) the operating procedures and the personnel shall be approved by a competent third-party. Tubes not conforming to this requirement shall be marked “C 1”.

7.3.4 The welding procedure for SAW tubes shall be qualified in accordance with Annex A.

7.3.5 The delivery condition of tubes covered by this Part of EN 10217 are shown in Table 1

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 1 — Tube manufacturing process, route and delivery condition

Route N°	Manufacturing process		Manufacturing route		Delivery condition
	process	symbols	Starting material	Forming operation	
1	Submerged arc welded	SAW	As (hot) rolled plate or strip	Cold formed	Normalised (entire tube)
2°	— longitudinal seam	— SAWL	Normalising rolled plate or strip	Cold formed	Without subsequent heat treatment [a]
2b			Normalised plate or strip		
3	— helical seam	— SAWH	As (hot) rolled plate or strip Normalised or normalising rolled plate or strip	Normalising formed [b]	Without subsequent heat treatment [a]

[a] Stress relieving treatment on the weld is permissible

[b] Only applicable to SAWL tubes

8 Requirements

8.1 General

When supplied in a delivery condition indicated in clause 7.3 and inspected in accordance with 9, 10 and 11, the tubes shall conform to the requirements of this Part EN 10217.

Tubes shall be suitable for hot and cold bending provided the bending is carried out in an appropriate manner.

In addition, the general technical delivery requirements specified in EN 10021 shall apply.

8.2 Chemical composition

8.2.1 Cast analysis

The cast analysis reported by the steel producer shall apply and conform to the requirements of Table 2.

NOTE. When welding tubes produced in accordance with this Part of EN 10217, account should be taken of the fact that the behaviour of the steel during and after welding is dependent not only on the steel, but also on the applied heat treatment and the conditions of preparing for and carrying out the welding.

8.2.2 Product analysis

Option 3: *A product analysis for the tube shall be supplied.*

Table 3 specifies the permissible deviations of the product analysis from the specified limits on cast analysis given in Table 2.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 2 — Chemical composition (cast analysis) [a], in % by mass

Steel grade		C	Si	Mn	P	S	Cr	Mo	Ni	Al_{tot}	Cu [b]	Nb	Ti	V	Cr+Cu +Mo+Ni
Steel name	Steel number		max		max	max	max		max		max	max	max	max	max
P235GH	1.0345	≤ 0,16	0,35	≤ 1,20	0,025	0,020	0,30	≤ 0,08	0,30	≥ 0,020 [c]	0,30	0,010 [d]	0,03 [d]	0,02 [d]	0,70
P265GH	1.0425	≤ 0,20	0,40	≤ 1,40	0,025	0,020	0,30	≤ 0,08	0,30	≥ 0,020 [c]	0,30	0,010 [d]	0,03 [d]	0,02 [d]	0,70
16Mo3	1.5415	0,12 to 0,20 [e]	0,35	0,40 to 0,90	0,025	0,020	0,30	0,25 to 0,35	0,30	≤ 0,040	0,30	-	-	-	-

[a] Elements not included in this Table shall not be intentionally added to the steel without the agreement of the purchaser, except for elements which may be added for finishing the cast. All appropriate measures shall be taken to prevent the addition of undesirable elements from scrap or other materials used in the steel making process.

[b] ***Option 2:*** *In order to facilitate subsequent forming operation, an agreed maximum copper content lower than indicated and an agreed specified maximum tin content shall apply.*

[c] This requirement is not applicable provided the steel contains a sufficient amount of other nitrogen binding elements which shall be reported. When using titanium, the producer shall verify that (Al+Ti/2) ≥ 0,020%.

[d] The content of these elements needs not to be reported unless intentionally added to the cast.

[e] For wall thickness ≥ 30 mm the carbon content may be increased by 0,02 % for cast and product analysis.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 3 — Permissible deviations of the product analysis from specified limits on cast analysis given in Table 2

Element	Limiting value for the cast analysis in accordance with Table 2 % by mass	Permissible deviation of the product analysis % by mass
C	≤ 0,20	± 0,02
Si	≤ 0,40	+ 0,05
Mn	≤ 1,00	± 0,05
	> 1,00 up to ≤ 1,40	+ 0,10
P	≤ 0,025	+ 0,005
S	≤ 0,020	+ 0,005
Al	≤ 0,040	± 0,005
Cr	≤ 0,30	+ 0,05
Cu	≤ 0,30	+ 0,05
Mo	≤ 0,35	± 0,03
Nb	≤ 0,010	+ 0,005
Ni	≤ 0,30	+ 0,05
Ti	≤ 0,03	+ 0,01
V	≤ 0,02	+ 0,01

8.3 Mechanical properties

8.3.1 Mechanical properties at and below room temperature

The mechanical properties at and below room temperature of the tubes of this Part of EN 10217 shall conform to the requirements in Table 4 and in clause 11.4.

8.3.2 Proof strength at elevated temperature

The minimum proof strength $R_{p0,2}$ values at elevated temperature are given in Table 5.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 4 — Mechanical properties at room temperature for wall thickness T up to and including 40 mm

Steel grade		Tensile properties at room temperature					Impact properties [a] [b]				
Steel name	Steel number	Upper yield strength or proof strength R_{eH} or $Rp_{0,2}$ for T (mm) min.		Tensile Strength Rm	Elongation[a] A min.		Minimum average absorbed energy KV. J at a temperature of °C				
		T ≤ 16	16 < T ≤ 40		%		l			t	
		MPa *	MPa *	MPa *	l	t	20	0	-10	20	0
P235GH	1.0345	235	225	360 to 500	25	23	-	40 [c]	28 [d]	-	27 [c]
P265GH	1.0425	265	255	410 to 570	23	21	-	40 [c]	28 [d]	-	27 [c]
16Mo3	1.5415	280	270	450 to 600	22	20	40 [c]	-	-	27 [c]	-

a l = longitudinal t = transverse

b To be verified when options 4 and/or 5 is/are specified.

c ***Option 4:*** *Impact energy shall be verified.*

d ***Option 5:*** *Longitudinal impact energy shall be verified.*

* 1 MPa = 1 N/mm^2

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 5 — Minimum proof strength Rp0,2 values at elevated temperature for wall thickness T up to and including 40 mm

Steel grade		Minimum proof strength $R_{p0,2}$ [a] MPa [*] at temperature of °C						
Steel name	Steel number	100	150	200	250	300	350	400
P235GH	1.0345	198	187	170	150	132	120	112
P265GH	1.0425	226	213	192	171	154	141	134
16Mo3	1.5415	243	237	224	205	173	159	156

[a] ***Option 6*** *: Proof strength $R_{p0,2}$ shall be verified at the testing temperature agreed at the time of enquiry and order*

[*] 1 MPa = 1 N/mm^2

8.4 Appearance and internal soundness

8.4.1 General

The weld area shall be free from cracks, lack of fusion and lack of penetration.

8.4.2 Appearance

8.4.2.1 The tubes shall be free from external and internal surface defects that can be detected by visual examination.

8.4.2.2 The internal and external surface finish of the tubes shall be typical of the manufacturing process and, where applicable, the heat treatment employed. Normally the finish and surface condition shall be such that any surface imperfections requiring dressing can be identified.

8.4.2.3 It shall be permissible to dress only by grinding or machining surface imperfections provided that after doing so, the wall thickness in the dressed area is not less than the specified minimum wall thickness. All dressed areas shall blend smoothly into the contour of the tube.

8.4.2.4 Any surface imperfection, which is demonstrated to be deeper than 5 % of the wall thickness T or 3 mm whichever is the smaller, shall be dressed.

This requirement does not apply to surface imperfection with a depth equal or less 0,3 mm.

8.4.2.5 Surface imperfections which encroach on the specified minimum wall thickness shall be considered defects and tubes containing these shall be deemed not to conform to with this Part of EN 10217.

8.4.2.6 Repairs of the weld seam are permitted in accordance with an established and agreed procedure.

8.4.3 Internal soundness

8.4.3.1 Leak Tightness

The tubes shall pass a hydrostatic test (see 11.6) for leak-tightness.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

8.4.3.2 Non-Destructive Testing

The full length of weld seam and the edges of plate or strip of tubes of test category 1 and category 2 shall be subjected to a Non-Destructive Testing for the detection of imperfections in accordance with 11.9.1.

Additionally the edges of plate or strip, the body and the ends of tubes of test category 2 shall be subjected to a Non-Destructive Testing for the detection of laminar imperfections in accordance with 11.9.2.

8.5 Straightness

The deviation from straightness of any tube length L shall not exceed 0,0015 L. Deviations from straightness over any one metre length shall not exceed 3 mm.

8.6 Preparation of ends

Tubes shall be delivered with square cut ends. The ends shall be free from excessive burrs.

Option 7: *The tubes shall be delivered with bevelled ends (see figure 1). The bevel shall have an angle α of 30° $^{+5°}_{0°}$ with a root face C of 1,6 mm $\pm$ 0,8 mm, except that for wall thicknesses T greater than 20 mm, an agreed alternative bevel may be specified*



Figure 1 — Tube end bevel

8.7 Dimensions, masses and tolerances

8.7.1 Diameter and wall thickness

Tubes shall be delivered by outside diameter D and wall thickness T.

Preferred outside diameters D and wall thickness T have been selected from ENV 10220 and are given in Table 6.

NOTE Dimensions which are different from those in Table 6 may be agreed.

8.7.2 Mass

For the mass per unit length the provision of ENV 10220 applies.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 6 — Preferred dimensions

dimensions in mm

Outside diameter D Series [a]			Wall thickness T																					
1	2	3	4	4,5	5	5,6	6,3	7,1	8	8,8	10	11	12,5	14,2	16	17,5	20	22,2	25	28	30	32	36	40
406,4																								
457																								
508																								
		559																						
610																								
		660																						
711																								
	762																							
813																								
		864																						
914																								
1 016																								
1 067																								
1 118																								
	1 168																							
1 219																								
	1 321																							
1 422																								
	1 524																							
1 626																								
	1 727																							
1 829																								
	1 930																							
2 032																								
	2 134																							
2 235																								
	2 337																							
	2 438																							
2 540																								

[a] series 1 = diameters for which all the accessories needed for the construction of piping system are standardised:

series 2 = diameters for which not all the accessories are standardised;

series 3 = diameters for special application for which very few standardised accessories exist..

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

8.7.3 Lengths

Unless option 8 is specified, the tubes shall be e delivered in random length. The delivery range shall be agreed at the time of enquiry and order.

Option 8: *The tubes shall be delivered in exact lengths, the length to be specified at the time of enquiry and order. For tolerances, see 8.7.4.5.*

8.7.4 Tolerances

8.7.4.1 Tolerances on diameter and thickness

The diameter and the wall thickness of the tubes shall be within the tolerance limits given in Table 7.

Table 7 — Tolerances on outside diameter and on wall thickness

dimension in mm

Tolerances on	Tolerances on T [a]	
D	T ≤ 5	5< T ≤ 40
± 0,75 % or ± 6 whichever is the smaller	± 10 % or ± 0,3 whichever is the greater	± 8 % or ± 2 whichever is the smaller
[a] The plus tolerance excludes the weld area (see 8.7.4.2)		

8.7.4.2 Height of the weld seam

The height of the external and internal weld seam shall be within the limits indicated in Table 8.

Table 8 — Maximum height of the weld seam

dimensions in mm

Wall thickness T	Maximum height of the outside and inside weld seam
T ≤ 12,5	3
T > 12,5	4

8.7.4.3 Radial offset of plate or strip edges at the weld

The radial offset of the abutting plate or strip edges shall within the limits indicated in Table 9.

Table 9 — Maximum radial offset of the abutting plate or strip edges

dimension in mm

Wall thickness T	Maximum radial offset
T ≤ 12,5	1,6
T > 12,5	0,125 T with a max. of 3,2

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

8.7.4.4 Misalignment of the weld seam

Misalignment of the weld seam shall be acceptable provided complete penetration and complete fusion are achieved.

8.7.4.5 The tolerances on exact length

The tolerances for exact lengths shall be as given in Table 10.

Table 10 — Tolerances on exact length

dimension in mm

Length 0L	Tolerance
$L \leq 6000$	+ 25 0
$6000 < L \leq 12000$	+ 50 0
$L > 12000$	+ By agreement 0

8.7.4.6 Out of roundness

The out-of-roundness (O) shall be calculated using the following equation:

$$O = \frac{D_{max} - D_{min}}{D} 100 \qquad (1)$$

where:

O = out-of-roundness in %
D = specified outside diameter in mm
D max, D min. = maximum and minimum outside diameter measured in the same plane in mm.

For tubes of outside diameter D = 406,4 mm, out-of-roundness, shall be included in the limits of the diameter tolerances.

For tubes of outside diameter $D > 406,4$ mm and with $D/T \leq 100$, out-of-roundness shall not exceed 2 %.

For tubes with a $D/T > 100$ the values for out-of-roundness shall be agreed at the time of enquiry and order.

〈A1〉 9 Inspection

9.1 Type of inspection

Conformity to the requirements of the order, for tubes in accordance with this Part of EN 10217, shall be checked by specific inspection.

When an inspection document 3.1.B is specified, the manufacturer shall state in the confirmation of the order whether he is operating according to a “quality assurance system”, certified by a competent body established within the community, and having undergone a specific assessment for materials and processes relevant to manufacture of welded tubes, including welding procedure approvals, welder/weld operator approval and NDT operator approval.

NOTE See Directive 97/23/EC Annex 1 section 4.3 third paragraph. 〈A1〉

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

9.2 Inspection documents

9.2.1 Types of inspection documents

Unless Option 9 is specified, an inspection certificate 3.1.B in accordance with EN 10204 shall be issued.

Option 9: *One of the inspection documents 3.1.A, 3.1.C or 3.2 in accordance with EN 10204 shall be issued.*

If an inspection document 3.1.A, 3.1.C or 3.2 is specified, the purchaser shall notify the manufacturer of the name and address of the organisation or person who is to carry out the inspection and produce the inspection document. In the case of the inspection report 3.2 it shall be agreed which party shall issue the certificate.

NOTE Document 3.1.A is not acceptable for compliance with the Directive 97/23/EC.

9.2.2 Content of inspection documents

The content of the inspection document shall be in accordance with EN 10168.

In all types of inspection documents a statement on the conformity of the products delivered with the requirements of this specification and the order shall be included.

The inspection certificate or inspection report shall contain the following codes and information:

— A Commercial transactions and parties involved;

— B description of products to which the inspection document applies;.

— C01-C03 location of the samples and direction of the test pieces and testing temperature;

— C10-C13 tensile test;

— C40-C43 impact test if applicable;

— C60-C69 other tests (e.g. flattening);

— C71-C92 chemical composition on cast analysis (product analysis if applicable);

— D01 marking and identification, surface appearance, shape and dimensional properties;

— D02-D99 leak-tightness test, NDT; material identification if applicable;

— Reference to welding procedure approval;

— Reference to welder and or welding operator approval;

— Reference to non-destructive testing operators approval;

— Z validation.

In addition for inspection document 3.1.B the manufacturer shall state the references to the certificate (see 9.1) of the appropriate “quality assurance system”, if applicable.

9.3 Summary of inspection and testing

Non-alloy steel tubes shall be inspected and tested in accordance with test category 1 or test category 2 as specified at the time of enquiry and order (see 6.1).

Tubes of steel grade 16Mo3 shall be inspected and tested in accordance with test category 2.

Inspection and testing to be carried out are summarised in Table 11.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table 11 — Summary of inspection and testing

Type of inspection and test		Frequency of testing	Refer to	Test category	
				1	2
Mandatory Tests	Cast analysis	one per cast	8.2.1 and 11.1	X	X
	Tensile test on base material at room temperature		8.3.1 and 11.2.1	X	X
	Tensile test on the weld at room temperature for tubes with D > 508 mm [a]	one sample per tube	8.3.1 and 11.3	X	X
	Weld bend test		8.3.1 and 11.4	X	X
	Hydrostatic leak tightness test	each tube	8.4.3.1 and 11.6	X	X
	Dimensional inspection	8.7 - 11.7		X	X
	Visual examination	11.8		X	X
	NDT of the weld		8.4.3.2 and 11.9.1	X	X
	NDT of base material for laminations		8.4.3.2 and 11.9.2.1	--	X
	NDT of tube ends for laminations	each tube	8.4.3.2 and 11.9.2.2	--	X
	NDT of plate/strip edges for laminations		8.4.3.2 and 11.9.2.3	--	X
	Material identification for steel grade 16Mo3		11.10	X	X
Optional Tests	Product analysis (option 3)	one per cast	8.2.2 and 11.1	X	X
	Tensile test at elevated temperature (option 6)	one per cast and same heat treatment condition	8.3.2 and 11.2.2	X	X
	Impact test on the base material at 20°C or 0°C (option 4)			X	X
	Longitudinal impact test on the base material for non- alloy steels at-10°C (option 5)	one per sample tube	8.3.1 and 11.5	X	X
	Impact test on the weld area at 20°C or 0°C [b] (option 11)			X	X
	Wall thickness measurement away from tube end (option 13)	8.7 and 11.7		X	X

[a] ***Option 10:*** *For tubes of outside diameter D less than or equal to 508 mm a transverse tensile test on the weld shall be carried out.*

[b] ***Option 11:*** *Impact test on the weld area shall be carried out.*

10 sampling

10.1 Frequency of tests

10.1.1 Test unit

For tubes delivered without subsequent heat treatment (see Table 1) a test unit shall comprise tubes of the same specified diameter and wall thickness, the same steel grade, the same cast, the same manufacturing process.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

For tubes which are furnace heat treated a test unit shall comprise tubes of the same specified diameter and wall thickness, the same steel grade, the same cast, the same manufacturing process, subjected to the same finishing treatment in a continuous furnace o heat treated in the same furnace charge in a batch - type furnace.

The maximum number of tubes per test unit shall be 50.

10.1.2 Number of sample tubes per test unit

The following number of sample tubes shall be selected from each test unit :

— test category 1: one sample tube per test unit;

— test category 2: two sample tubes per test unit; when the total number of tubes is less than 20, only one tube shall be sampled.

10.2 Preparation of samples and test pieces

10.2.1 Selection and preparation of samples for product analysis

Samples for product analysis shall be taken from the test pieces or samples for mechanical testing or from the whole thickness T of the tube at the same location as for the mechanical test samples, in accordance with ISO 14284.

10.2.2 Location, orientation and preparation of samples and test pieces for mechanical tests

10.2.2.1 General

Samples and test pieces shall be taken at the tube ends and in accordance with the requirements of EN ISO 377.

10.2.2.2 Test pieces for tensile tests of the base material

The test piece for the tensile test at room temperature shall be taken in accordance with the requirements of EN 10002-1.

The test piece for the tensile test at elevated temperature shall be taken in accordance with the requirements of EN 10002-5.

At the manufacturer's discretion the test piece shall be either a machined test piece with circular cross section from an unflattened sample or a strip section and be taken in a direction either longitudinal or transverse to the axis of the tube.

The test piece shall be taken diametrically opposite the weld; for helically submerged arc-welded tubes (SAWH) the test piece shall be taken at 1/4 of the distance between the welds.

10.2.2.3 Test pieces for tensile tests on the weld

The test piece shall be taken transverse to the weld with the weld at the centre of the test piece. The test piece shall be a strip section with the full thickness of the tube; the weld bead may be removed.

10.2.2.4 Weld bend test

The test pieces for the weld bend test at the root and face shall be taken and prepared in accordance with EN 910.

10.2.2.5 Test pieces for the impact test

Three standard Charpy V-notch test pieces shall be prepared in accordance with EN 10045-1. If the wall thickness is such that standard test pieces cannot be produced without flattening of the section, then test pieces of width less than 10 mm, but not less than 5 mm shall be prepared; the largest obtainable width shall be used.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Where test pieces at least 5 mm width cannot be obtained, the tubes shall not be subjected to impact testing.

Unless otherwise specified (see option 5), the test pieces shall be taken transverse to the tube axis unless D_{min} , as calculated by the following equation, is greater than the specified outside diameter, in which case longitudinal test pieces shall be used:

$D_{min} = (T-5) + [\ 756{,}25 / (T-5)\ ]$ (2)

The test pieces for the impact test on base material shall be taken diametrically opposite the weld; for helically submerged arc-welded tubes (SAWH) the test piece shall be taken at 1/4 of the distance between the welds.

The location of the test pieces for the impact test of the weld area (see option 11) shall be agreed at the time of enquiry and order.

The test pieces shall be prepared such that the axis of the notch is perpendicular to the surface of the tube see figure 2.

Key:

1 Longitudinal test piece

2 transverse test piece



Figure 2 — Impact test piece orientation

11 Test methods

11.1 Chemical analysis

The elements to be determined and reported shall be those specified in Table 2. The choice of a suitable physical or the chemical analytical method for the analysis shall be at the discretion of the manufacturer. In case of dispute the method used shall be agreed between manufacturer and purchaser taking into account CR 10261.

11.2 Tensile test on the base material

11.2.1 At room temperature

The test shall be carried out at room temperature in accordance with EN 10002-1, and the following determined:

— the tensile strength (R_m);

— the upper yield strength (R_{eH}) or if a yield phenomenon is not present the 0,2 % proof strength ($R_{p0,2}$);

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

— the percentage elongation after fracture with a reference to a gauge length (L_0) of $5{,}65 \cdot \sqrt{So}$; if a non-proportional test piece is used, the percentage elongation value shall be converted to the value for a gauge length $Lo = 5{,}65 \cdot \sqrt{So}$ using the conversion tables in EN ISO 2566-1.

11.2.2 At elevated temperature

The test shall be carried out in accordance with EN 10002-5 at the temperature agreed at the time of enquiry and order and the proof strength ($R_{p0,2}$) shall be determined.

11.3 Traverse tensile test on the weld

The test shall be carried out in accordance with EN 10002-1 at room temperature and the tensile strength (R_m) shall be determined.

11.4 Weld bend test

The test shall be carried out in accordance with EN 910 using a mandrel of a diameter of 3T. After testing the test piece shall show no cracks or flaws but slight premature failure at its edges shall not be regarded as a justification for rejection.

11.5 Impact test

11.5.1 The test shall be carried out in accordance with EN10045-1 at the temperature given in Table 4.

11.5.2 The mean value of the three test pieces shall meet the requirement given in Table 4. One individual value may be below the specified value, provided that it is not less than 70 % of that value.

11.5.3 If the width (W) of the test piece is less than 10 mm, the measured impact energy (KV_p) shall be converted to impact energy(KV_c) using the following equation:

$$KVc = \frac{10xKVp}{W} \qquad (3)$$

where:

— KV_c is the calculated impact energy, in J;

— KV_p is the measured impact energy, in J;

— W is the width of the test piece, in mm.

The calculated impact energy KV_c shall conform to the requirements given in 11.5.2.

11.5.4 If the requirements of 11.5.2 are not met, then an additional set of three test pieces may be taken at the discretion of the manufacturer from the same sample and tested. To consider the test unit as conforming, after testing the second set, the following conditions shall be satisfied simultaneously:

the average value of the six tests shall be equal to or greater than the specified minimum average value;

not more than two of the six individual values may be lower than the specified minimum average value;

not more than one of the six individual values may be lower than 70 % of the specified minimum average value.

11.5.5 The dimensions in millimetres of the test pieces, the measured impact energy values and the resulting average value shall be reported.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

11.6 Hydrostatic leak tightness test

The hydrostatic leak-tightness test shall be carried out at a test pressure of 70 bar[2)] or at a test pressure P calculated using the following equation, whichever is lower:

$$P = 20\frac{SxT}{D} \qquad (4)$$

where:

— P is the test pressure, in bar;

— D is the specified outside diameter, in mm;

— T is the specified wall thickness, in mm;

S is the stress, in MPa, corresponding to 70 % of the specified minimum yield strength (see Table 4) for the steel grade concerned.

The test pressure shall be held for not less than 5 s for tubes with an outside diameter D less than or equal to 457 mm and for not less than 10 s for tubes with an outside diameter D greater than 457 mm.

The tube shall withstand the test without showing leakage or visible deformation.

NOTE This hydrostatic leak-tightness test is not a strength test.

***Option 12**: A test pressure different from that specified in 11.6 and corresponding to stress below 90% of the specified minimum yield strength (see Table 4) for the steel grades concerned is specified.*

11.7 Dimensional inspection

Specified dimensions, including straightness, shall be verified.

The outside diameter shall be measured across the diameter or using a circumference tape at the tube ends.

Unless option 13 is specified the wall thickness shall be measured at both tube ends.

***Option 13:** The wall thickness shall be measured away from the tube ends in accordance with an agreed procedure.*

11.8 Visual examination

Tubes shall be visually examined to ensure conformity to the requirements of 8.4.1 and 8.4.2.

11.9 Non-Destructive Testing

11.9.1 Non-Destructive Testing of the weld seam

The full length of the weld seam of tubes shall be tested in accordance with either EN 10246-9 to acceptance level U3 for test categories 1 and level U2 for test category 2 or to EN 10246-10 to image quality class R2.

Unless option 14 is specified, the selection of the test inspection method is at the discretion of the manufacturer.

***Option 14:** The test inspection method is specified by the purchaser*

---

2) 1 bar = 100 kPa

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Option 15: *The image quality class R1 of EN 10246-10 shall be applied for the radiographic inspection of the weld seam.*

Weld seam at the tube ends not automatically tested shall either be subjected either to manual/semiautomatic ultrasonic testing or to radiographic testing using the same method as specified above or be cropped off.

11.9.2 Non-Destructive Testing for the detection of laminations for tubes of test category 2

11.9.2.1 The base material shall be tested in accordance with EN 10246-15 with acceptance level U2.

11.9.2.2 The tube ends shall be tested in accordance with EN 10246-17. Laminar imperfections greater than 6 mm in the circumferential direction are not permitted within 25 mm at the tube ends.

11.9.2.3 The strip/plate edges adjacent to the weld seam shall be tested in accordance with either EN 10246-15 or EN10246-16 with acceptance level U2 within a 15 mm zone along the weld seam.

11.9.3 Non-Destructive Testing of strip end welds

Strip end welds for helically welded tubes shall be tested in accordance with 11.9.1 and 11.9.2.

11.10 Material identification

The tubes made of steel grade 16Mo3 shall be tested to assure that the correct grade is being supplied.

11.11 Retests, sorting and reprocessing

For retest, sorting and reprocessing the requirements of EN 10021 apply.

12 Marking

12.1 Marking to be applied

The marking shall be marked indelibly on each tube at least at one end.

The marking shall include the following information:

— the manufacturer's name or trade mark;

— the type of the tubes (symbols in accordance with Table 1);

— the number of this European standard and the steel name (see 5.2);

— the test category in case of non-alloy steel grades;

— the category conformity indicator, if applicable (see 7.3.1 and 7.3.3).

— the cast number or a code number;

— the mark of the inspection representative

— an identification number (e.g. order or item number) which permits the correlation of the product or delivery unit to the related document;

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Example of marking:

X – SAWL - EN 10217-5 - P265GH - TC1 – C1 - Y - Z_1 - Z_2

where:

— X is the manufacturer's mark;

— SAWL is the type of tube;

— TC1 is the designation of the test category 1;

— C1 is the category conformity indicator;

— Y is the cast number or a code number;

— Z_1 is the mark of the inspection representative;

— Z_2 is the identification number.

12.2 Additional marking

Option 16: *Additional marking, as agreed upon at the time of enquiry and order, shall be applied.*

13 Protection

The tubes shall be delivered without a temporary protective coating.

Option 17: *A temporary protective coating or durable coating and/or lining shall be applied.*

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Annex A (normative)

Qualification of welding procedure

A.1 General

Submerged arc weld tube produced to this Part of EN 10217 shall be welded in accordance with set procedures which have been specified, qualified and/or approved in accordance with this annex.

This annex does not invalidate previous welding procedures qualified and/or approved to meet national standards or specifications, providing the content of the requirements is satisfied and the previous procedure qualifications and/or approvals are relevant to the applications and production work on which they are to be employed.

This annex covers the requirements for the qualification and/or approval of weld procedures for the production of SAW tube including inspection and testing and also for other fusion welding processes used in SAW tube production.

A.2 Welding procedure specification

The qualification for the welding procedure shall be carried out in accordance with a welding procedure specification (WPS). The specification shall include the following information as a minimum requirement.

A.2.1 Parent metal

A.2.1.1 Steel name or number

The steel grade shall be identified in accordance with the requirements of this Part of EN 10217.

NOTE A welding procedure specification may cover a group of materials (see A.8.1).

A.2.1.2 Tube dimensions

Tube dimensions shall be supplied for the following:

outside diameter D;

wall thickness T.

A.2.2 Weld preparation

Details of the strip/plate edge profile prior to welding shall be given. This may be in the form of a dimensional sketch. Details of the methods of preparation and tack welding shall be included.

A.2.3 Filler wires and fluxes

A.2.3.1 The standard number and grade shall be referenced.

A.2.3.2 The number, dimensions and position of filler wire or wires and details of any additional filler metal shall be supplied. When specifying the position, any angular variation shall be included, if applicable.

A.2.3.3 If carried out, the flux recycling procedure shall be referenced.

A.2.4 Electrical parameters

Details of the electrical parameters shall include as a minimum:

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

type of current (a.c. and/or d.c.) and polarity;

nominal current, the range to be expressed as a plus and minus percentage;

nominal arc voltage, the range to be expressed as a plus and minus percentage.

A.2.5 Mechanical parameters

Details of mechanical parameters shall include as a minimum:

nominal travel speed, the range to be expressed as a plus and minus percentage;

number and order of inside and outside weld runs.

A.2.6 Heat input (kJ/mm)

If required the maximum value achieved during the qualification/approval test shall be recorded.

A.2.7 Preheat temperature

If required the minimum preheat temperature shall be specified.

A.2.8 Interpass temperature

The maximum permissive interpass temperature shall be specified where applicable.

A.2.9 Postweld heat treatment

The delivery condition after welding shall be in accordance with Table 1 for the steel grade concerned.

Details of the heat treatment, where applicable, shall be included on the qualification documentation.

A.2.10 Example of welding procedure specification form

A typical weld procedure specification is shown in Table A.1, for information.

Table A.1 Example of typical welding procedure specification form

Welding procedure specification										
Ref. N. WPS:			Prepared by:			Checked by:				Date:
Parent metal:						Thickness/diameter:				
Weld preparation:						Pass location:				
Preparation method			Machined/plasma or falme cut							
Pass n.	Wire n.	Welding position	Wire					Nominal current	Nominal arc voltage	Nominal travel speed
			Size mm	Code n.	Designation	Polarity	Flux	A	V	mm/s
Heat imput [a]								Preheat		°C min
Heat treatment			Stress relieving			Normalizing		Interpass temperature		°C max
Heating rate								NDT		
Soaking temperature										
Soaking time										
Cooling rate										
Withdraw temperature										
Notes										
[a] If required										

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

A.3 Preparation of sample tube and sample

A.3.1 Sample tube

Preparation and welding of sample tube shall be carried out in accordance with the WPS and under the general conditions of production welding which they shall represent.

When an approved procedure is required the name and address of the authorised body shall be supplied.

A.3.2 Sample

A test sample sufficiently long to carry out the testing requirements in clause A.5 shall be taken from the end of the tube after welding, in the delivery condition specified in Table 1.

A.4 Inspection and testing of the weld

The test sample shall be subjected to the inspection or testing of Table A.2.

Table A.2 Inspection and testing of the weld

Type of inspection or test	Extent or number of test pieces
Visual examination of the weld [a]	100% of the sample
Radiographic examination of the weld	100% of the sample
Weld bend test	2 root and 2 face test pieces [b]
Macro-examination of weld cross section	1 specimen
Transverse weld tensile test	2 test pieces
Weld impact test	3 sets of three test pieces

[a] Magnetic particle inspection or penetrant inspection may be used at the discretion of the manufacturer.

[b] These tests may be replaced by 4 side bend tests for wall thicknesses greater than 12,5 mm, at the manufacturer's discretion.

A.5 Weld test pieces

A.5.1 Bend test pieces

The bend test pieces shall be prepared in accordance with 10.2.2.4.

A.5.2 Macro-examination

The sample shall be prepared in accordance with EN 1321.

A.5.3 Transverse tensile test

The transverse tensile test piece shall be prepared in accordance with EN 895.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

A.5.4 Impact test

Three sets of three standard Charpy V-notch test pieces taken transverse to the weld shall be prepared in accordance with 10.2.2.5.

A.6 Test methods

A.6.1 Visual examination

Visual examination of the test piece shall be carried out.

A.6.2 Radiographic test

The radiographic test shall be carried out in accordance with 11.9. 1.

A.6.3 Weld bend test

The weld bend test shall be carried out in accordance with 11.4.

A.6.4 Macro-examination

The macro-examination shall be carried out at a magnification of × 5.

A.6.5 Transverse weld tensile test

The transverse weld tensile test shall be carried out in accordance with 11.3.

A.6.6 Weld impact test

The weld impact test shall be carried out in accordance with 11.5.

A.7 Test acceptance levels

A.7.1 Visual examination

Cracks shall not be permitted.

A.7.2 Radiographic test

This shall meet the acceptance requirements of 11.9.1.

A.7.3 Weld bend test

The tested specimen shall be checked for lack of fusion and the results reported.

For acceptance the results shall meet the requirements of 11.4.

A.7.4 Macro-examination

The specimen shall be checked for the following:

— cracks

— lack of penetration;

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

— lack of fusion;

— height of internal and external weld beads;

— radial offset of plate edges;

— misalignment of weld seam.

The result shall be recorded.

For acceptance the following apply:

— cracks and lack of penetration and fusion shall not be permitted;

— height of internal and external weld beads, radial offset of plate and strip edges and misalignment of weld seam shall comply with the requirements of Tables 8 and 9 and clause 8.7.4.4 respectively.

A.7.5 Transverse weld tensile test

The value of R_m shall be determined and meet the requirements of 11.3 and of Table 4 for the steel grade concerned. The position of the fracture shall be reported.

A.7.6 Weld impact test

The impact test results shall meet the requirements of 11.5 and Table 4 for the steel grade concerned.

A.7.7 Example of test result document

A typical test results form is shown in Table A.3, for information.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Table A.3 Example of typical test results form

Test results					
Manufacturer: Welding procedure Reference no: Visual examination: Pass/fail Penetrant/magnetic particle test Pass/fail				Examiner or examining body: Reference no: Radiographic test [a]: Pass/fail Ultrasonic examination [a]: Temperature: °C	
Tensile tests					
Type /No.	Rm MPa	Fracture location		Remarks	
Requirements					
Bend tests Former diameter			Macro examination		
Type /No.	Bend angle	Results			
Impact test [a] Type:		Size:		Requirement:	
Notch Location/Direction	Temperature °C	Values J			Remarks
		1	2	3 / Average	
Hardness test [a] Type/load: H. A. Z.: Weld Metal: Parent metal:					
Other tests:					
Remarks:					
Tests carried out in accordance with the requirements of:					
Examiner or examining body:					
Laboratory report reference no:					
Test results were acceptable/not acceptable (delete as appropriate)					
Test carried out in the presence of:					
Name:	Signature:	Date:			
[a] If required.					

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

A.8 Range of use of qualified procedures

A.8.1 Materials groups

In order to avoid unnecessary qualification of weld procedures similar types of material have been grouped together and are shown in Table A.4.

A procedure qualified for any material within a group covers all other materials within that group.

Table A.4 Grouping system for SAW steel tubes

Group	Steel grades	
	Steel name	Steel number
1	P235GH	1.0345
	P265GH	1.0425
2	16Mo3	1.5415

A.8.2 Materials thickness

Qualification at a given wall thickness covers a range of wall thicknesses and these are shown in Table A.5.

Table A.5 Range of qualification based on wall thickness T

dimension in mm

Wall thickness of sample tube	Range of qualification
$T \leq 12,5$	3 to 2 T
$T > 12,5$	0,5 T to 2 T

A.8.3 Filler wire classification

The qualification of a filler wire covers other filler wires provided they meet the following requirement:

they shall be in the same group of steels as defined in Table A.4;

they shall have the same nominal chemical composition.

A.8.4 Welding flux

A change from one welding flux, as defined by EN 760, to one of a different classification shall require a separate welding procedure qualification.

A.8.5 Other parameters

Changes simply or collectively, to the number of the welding wires or the type of current (e.g. from a.c. to d.c.) or changes in the number of weld runs per side from single to multi-pass, or vice versa, shall require one or more separate welding procedure specification(s) and approval(s).

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

A.9 Qualification record

The manufacturer shall state that each welding procedure has been qualified and the procedure and qualification test results shall be documented and signed by his authorised representative (see Table A.3).

When the testing and inspection have been witnessed and approved by an authorised body the documentation shall contain the name and address of the person or company and be signed by the person approving the procedure.

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Annex ZA
(informative)

A1 Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association to provide a means of conforming to Essential Requirements of the New Approach Directive 97/23/EC.

Once this standard is cited in the Official Journal of the European Union under that Directive and has been implemented as a national standard in at least one Member State, compliance with the clauses of this standard given in table ZA-1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding Essential Requirements of that Directive and associated EFTA regulations.

Table ZA-1 — Correspondence between this European standard and Directive 97/23/EC

Clauses/sub-clauses of this EN	Pressure Equipment Directive 97/23/EC Annex I	Content
7.3.3	3.1.2	Welding
7.3.1	3.1.3	NDT personnel
8.3	4.1a	Appropriate material properties
7.2 and 8.2 Table 2 and Table 5	4.1c	Ageing
7.3 and 8.4	4.1d	Suitable for the processing procedures
9 - 10	4.3	Documentation

WARNING: Other requirements and other EC Directives may be applicable to the product(s) falling within the scope of this standard. A1

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

Bibliography

EN 473, *Non destructive testing - Qualification and certification of NDT personnel - General principles*

EN 10233, *Metallic materials - Tubes - Flattening test.*

EN 10234, *Metallic materials - Tubes - Drift expanding test.*

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

blank

Licensed Copy: Institute Of Technology Tallaght, Institute of Technology, Tue Sep 12 10:27:28 BST 2006, Uncontrolled Copy, (c) BSI

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at http://www.bsi-global.com.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at http://www.bsi-global.com/bsonline.

Further information about BSI is available on the BSI website at http://www.bsi-global.com.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI
389 Chiswick High Road
London
W4 4AL