

Flat products made of steels for pressure purposes

Part 4: Nickel alloy steels with specified low temperature properties

ICS 77.140.30; 77.140.50

National foreword

This British Standard is the UK implementation of EN 10028-4:2009. It supersedes BS EN 10028-4:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/73/2, Steel plates and bars for pressure purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2009.
© BSI 2009

ISBN 978 0 580 64187 9

Amendments/corrigenda issued since publication

Date	Comments

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10028-4

June 2009

ICS 77.140.30; 77.140.50

Supersedes EN 10028-4:2003

English Version

**Flat products made of steels for pressure purposes - Part 4:
Nickel alloy steels with specified low temperature properties**

Produits plats en aciers pour appareils à pression - Partie
4: Aciers alliés au nickel avec caractéristiques spécifiées à
basse température

Flacherzeugnisse aus Druckbehälterstählen - Teil 4:
Nickellegierte kaltzähe Stähle

This European Standard was approved by CEN on 14 May 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Dimensions and tolerances on dimensions	4
5 Calculation of mass	4
6 Classification and designation	4
6.1 Classification.....	4
6.2 Designation	4
7 Information to be supplied by the purchaser	4
7.1 Mandatory information.....	4
7.2 Options	5
7.3 Example for ordering.....	5
8 Requirements	5
8.1 Steelmaking process	5
8.2 Delivery condition.....	5
8.3 Chemical composition	5
8.4 Mechanical properties.....	6
8.5 Surface condition.....	9
8.6 Internal soundness	9
9 Inspection	9
9.1 Types of inspection and inspection documents	9
9.2 Tests to be carried out	9
9.3 Retests	9
10 Sampling	9
11 Test methods.....	9
12 Marking	9
Annex A (informative) Guidelines for heat treatment	10
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC	11
Bibliography	12

Foreword

This document (EN 10028-4:2009) has been prepared by Technical Committee ECISS/TC 22 “Steels for pressure purposes - Qualities”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2009, and conflicting national standards shall be withdrawn at the latest by December 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10028-4:2003.

This European Standard consists of the following parts, under the general title *Flat products made of steels for pressure purposes*:

- *Part 1: General requirements*
- *Part 2: Non-alloy and alloy steels with specified elevated temperature properties*
- *Part 3: Weldable fine grain steels, normalized*
- *Part 4: Nickel alloy steels with specified low temperature properties*
- *Part 5: Weldable fine grain steels, thermomechanically rolled*
- *Part 6: Weldable fine grain steels, quenched and tempered*
- *Part 7: Stainless steels*

NOTE The clauses marked by two points (••) contain information relating to agreements that may be made at the time of enquiry and order.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 97/23/EC.

For relationship with EU Directive 97/23/EC, see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies requirements for flat products for pressure equipment made of nickel alloy steels as specified in Table 1.

The requirements and definitions of EN 10028-1:2007 + A1:2009 also apply.

NOTE Once this European Standard is published in the EU Official Journal (OJEU) under Directive 97/23/EC, presumption of conformity to the Essential Safety Requirements (ESRs) of Directive 97/23/EC is limited to technical data of materials in this European Standard (Part 1 and this Part 4 of the series) and does not presume adequacy of the material to a specific item of equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of Directive 97/23/EC are satisfied, needs to be done.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10028-1:2007 + A1:2009, *Flat products made of steels for pressure purposes – Part 1: General requirements*

EN 10204:2004, *Metallic products – Types of inspection documents*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10028-1:2007 + A1:2009 apply.

4 Dimensions and tolerances on dimensions

See EN 10028-1:2007 + A1:2009.

5 Calculation of mass

See EN 10028-1:2007 + A1:2009,

6 Classification and designation

6.1 Classification

In accordance with EN 10020, all steel grades covered by this document are alloy special steels.

6.2 Designation

See EN 10028-1:2007 + A1:2009.

7 Information to be supplied by the purchaser

7.1 Mandatory information

See EN 10028-1:2007 + A1:2009.

7.2 Options

A number of options are specified in this European Standard and listed below. Additionally the relevant options of EN 10028-1:2007 + A1:2009 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see also EN 10028-1:2007 + A1:2009).

- 1) delivery condition other than that specified in Table 3 (see 8.2.2);
- 2) delivery of products in the untreated condition (see 8.2.3);
- 3) specification of a minimum impact energy of 40 J (see NOTE to 8.4 and Table 4);
- 4) mid thickness test pieces for the impact test (see Clause 10);
- 5) verification of impact energy for longitudinal test pieces (see Clause 11).

7.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name 15NiMn6 and the number 1.6228 as specified in EN 10028-4, to be delivered with inspection document 3.1 as specified in EN 10204.

10 plates – 50 x 2000 x 10 000 – EN 10028-4 15NiMn6 – Inspection document 3.1

or

10 plates – 50 x 2000 x 10 000 – EN 10028-4 1.6228 – Inspection document 3.1.

8 Requirements

8.1 Steelmaking process

See EN 10028-1:2007 + A1:2009.

8.2 Delivery condition

8.2.1 The delivery condition shall be noted in the inspection document.

8.2.2 •• Unless otherwise agreed at the time of enquiry and order, the products covered by this document shall be supplied in the usual delivery conditions specified in Table 3.

8.2.3 •• If so agreed at the time of enquiry and order, the products may be supplied in the untreated condition.

In these cases, the specified tests shall be carried out on test pieces in the usual delivery condition as given in Table 3.

NOTE Testing in a simulated heat treated condition does not discharge the processor from the obligation of providing proof of the specified properties in the finished product.

8.3 Chemical composition

8.3.1 The requirements of Table 1 shall apply for the chemical composition according to the cast analysis.

8.3.2 The product analysis shall not deviate from the specified values for the cast analysis as specified in Table 1 by more than the values given in Table 2.

Table 1 — Chemical composition (cast analysis) ^a

Steel grade		% by mass									
Steel name	Steel number	C max.	Si max.	Mn	P max.	S max.	Al _{total} min.	Mo max.	Nb max.	Ni	V max.
11MnNi5-3	1.6212	0,14	0,50	0,70 to 1,50	0,025	0,010	0,020	—	0,05	0,30 ^b to 0,80	0,05
13MnNi6-3	1.6217	0,16	0,50	0,85 to 1,70	0,025	0,010	0,020	—	0,05	0,30 ^b to 0,85	0,05
15NiMn6	1.6228	0,18	0,35	0,80 to 1,50	0,025	0,010	—	—	—	1,30 to 1,70	0,05
12Ni14	1.5637	0,15	0,35	0,30 to 0,80	0,020	0,005	—	—	—	3,25 to 3,75	0,05
X12Ni5	1.5680	0,15	0,35	0,30 to 0,80	0,020	0,005	—	—	—	4,75 to 5,25	0,05
X8Ni9	1.5662	0,10	0,35	0,30 to 0,80	0,020	0,005	—	0,10	—	8,5 to 10,0	0,05
X7Ni9	1.5663	0,10	0,35	0,30 to 0,80	0,015	0,005	—	0,10	—	8,5 to 10,0	0,01

^a Elements not listed in this Table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate measures shall be taken to prevent the addition from scrap or other materials used in steelmaking of these elements which may adversely affect the mechanical properties and usability. The content of Cr + Cu + Mo shall not exceed 0,50 %.

^b For product thicknesses ≤ 40 mm, a minimum nickel content of 0,15 % is permitted.

Table 2 — Permissible product analysis tolerances on the limiting values given in Table 1 for the cast analysis

Element	Specified value in the cast analysis according to Table 1	Permissible deviation ^a of the product analysis
	% by mass	% by mass
C	≤ 0,18	+ 0,02
Si	≤ 0,50	+ 0,05
Mn	≤ 1,00	± 0,05
	> 1,00 to ≤ 1,70	± 0,10
P	≤ 0,015	+ 0,003
	> 0,015 to ≤ 0,025	+ 0,005
S	≤ 0,010	+ 0,003
Al	≥ 0,020	- 0,005
Mo	≤ 0,10	+ 0,03
Nb	≤ 0,05	+ 0,01
Ni	≤ 0,85	± 0,05
	> 0,85 to ≤ 3,75	± 0,07
	> 3,75 to ≤ 10,0	± 0,10
V	≤ 0,05	+ 0,01

^a If several product analyses are carried out on one cast, and the contents of an individual element determined lie outside the permission range of the chemical composition specified for the cast analysis, then it is only allowed to exceed the permissible maximum value or fall short of the permissible minimum value, but not both for one cast.

8.4 Mechanical properties

The values given in Tables 3 and 4 (see also EN 10028-1:2007 + A1:2009 and clause 10) shall apply.

NOTE Optionally, for steel grades 11MnNi5-3, 13MnNi6-3, 15NiMn6, 12Ni14 and X12Ni5, a minimum impact energy value of 40 J may be specified for temperatures where lower minimum values are specified (see Table 4, footnote d).

Table 3 — Mechanical properties at room temperature

Steel grade		Usual delivery condition ^{a,b} (Heat treatment symbol)	Product thickness	Yield strength	Tensile strength	Elongation after fracture
Steel name	Steel number		t mm	R_{eH} MPa min.	R_m MPa	A % min.
11MnNi5-3	1.6212	+N (+NT)	≤ 30	285	420 to 530	24
			30 < t ≤ 50	275		
			50 < t ≤ 80	265		
13MnNi6-3	1.6217	+N (+NT)	≤ 30	355	490 to 610	22
			30 < t ≤ 50	345		
			50 < t ≤ 80	335		
15NiMn6	1.6228	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < t ≤ 50	345		
			50 < t ≤ 80	335		
12Ni14	1.5637	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < t ≤ 50	345		
			50 < t ≤ 80	335		
X12Ni5	1.5680	+N or +NT or +QT	≤ 30	390	530 to 710	20
			30 < t ≤ 50	380		
X8Ni9 +NT640 ^a	1.5662 +NT640 ^a	+N plus +NT	≤ 30	490	640 to 840	18
			30 < t ≤ 50	480		
X8Ni9 +QT640 ^a	1.5662 +QT640 ^a	+QT	≤ 30	490		
			30 < t ≤ 50	480		
X8Ni9 +QT680 ^a	1.5662 +QT680 ^a	+QT ^c	≤ 30	585	680 to 820	18
			30 < t ≤ 50	575		
X7Ni9	1.5663	+QT ^c	≤ 30	585	680 to 820	18
			30 < t ≤ 50	575		
^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.						
^b For temperatures and cooling conditions, see Table A.1.						
^c For product thickness < 15 mm, delivery conditions +N plus +NT are also applicable.						

Table 4 — Minimum impact energy values

Steel grade		Heat treatment condition ^{a,b}	Product thickness mm	Direction	Minimum impact energy KV in J													
Steel name	Steel number				at a temperature in °C of													
					20	0	-20	-40	-50	-60	-80	-100	-120	-150	-170	-196		
11MnNi5-3	1.6212	+N (+NT)	≤ 80	longitudinal	70	60	55	50	45	40	—	—	—	—	—	—		
13MnNi6-3	1.6217			transverse	50	50	45	35 ^d	30 ^d	27 ^d	—	—	—	—	—	—	—	
15NiMn6	1.6228	+N or +NT or +QT		longitudinal	65	65	65	60	50	50	40	—	—	—	—	—	—	
				transverse	50	50	45	40	35 ^d	35 ^d	27 ^d	—	—	—	—	—	—	
12Ni14	1.5637	+N or +NT or +QT		longitudinal	65	60	55	55	50	50	45	40	—	—	—	—	—	
				transverse	50	50	45	35 ^d	35 ^d	35 ^d	30 ^d	27 ^d	—	—	—	—	—	
X12Ni5	1.5680	+N or +NT or +QT	≤ 50	longitudinal	70	70	70	65	65	65	60	50	40 ^c	—	—	—		
				transverse	60	60	55	45	45	45	40	30 ^d	27 ^{c,d}	—	—	—		
X8Ni9+NT640; X8Ni9+QT640 ^a	1.5662+NT640; 1.5662+QT640 ^a	+N plus +NT; +QT		longitudinal	100	100	100	100	100	100	100	90	80	70	60	50		
				transverse	70	70	70	70	70	70	70	60	50	50	45	40		
X8Ni9 +QT680 ^a	1.5662 +QT680 ^a	+QT		longitudinal	120	120	120	120	120	120	120	110	100	90	80	70		
				transverse	100	100	100	100	100	100	100	90	80	70	60	50		
X7Ni9	1.5663	+QT		longitudinal	120	120	120	120	120	120	120	120	120	120	120	110	100	
				transverse	100	100	100	100	100	100	100	100	100	100	100	90	80	

^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.

^b For temperatures and cooling conditions, see Table A.1.

^c The values are applicable for product thicknesses ≤ 25 mm at –110 °C and for product thicknesses of 25 mm < t ≤ 30 mm at –115 °C.

^d ●● A minimum impact energy value of 40 J may be agreed at the time of enquiry and order.

8.5 Surface condition

See EN 10028-1:2007 + A1:2009.

8.6 Internal soundness

See EN 10028-1:2007 + A1:2009.

For possible verification of internal soundness, see also EN 10028-1:2007 + A1:2009.

9 Inspection

9.1 Types of inspection and inspection documents

See EN 10028-1:2007 + A1:2009.

9.2 Tests to be carried out

See EN 10028-1:2007 + A1:2009.

9.3 Retests

See EN 10028-1:2007 + A1:2009.

10 Sampling

See EN 10028-1:2007 + A1:2009.

•• For the impact test, deviating from EN 10028-1:2007 + A1:2009, Table 3, footnote f, the preparation of test pieces taken from the mid thickness may be agreed at the time of enquiry and order. In this case, test temperatures and minimum impact energy values shall also be agreed.

11 Test methods

See EN 10028-1:2007 + A1:2009.

•• For the impact test, verification of impact energy for longitudinal test pieces may be agreed at the time of enquiry and order in accordance with 10.2.2.3 and 11.4 in EN 10028-1:2007 + A1:2009.

12 Marking

See EN 10028-1:2007 + A1:2009.

NOTE For the grade X8Ni9 the relevant heat treatment variant (+NT640 or +QT640 or +QT680) belongs to the steel name or steel number.

Annex A (informative)

Guidelines for heat treatment

Reference data on heat treatment temperatures and cooling media are given in Table A.1.

Table A.1 — Guidelines on the temperatures and cooling media of heat treatment

Steel grade		Heat treatment condition ^a	Heat treatment			
Steel name	Steel number		Austenitizing °C	Cooling ^b	Tempering °C	Cooling ^b
11MnNi5-3	1.6212	+N (+NT)	880 to 940	a	580 to 640	a
13MnNi6-3	1.6217	+N (+NT)	880 to 940	a	580 to 640	a
15NiMn6	1.6228	+N	850 to 900	a	-	-
		+NT	850 to 900	a	600 to 660	a or w
		+QT	850 to 900	w or o	600 to 660	a or w
12Ni14	1.5637	+N	830 to 880	a	-	-
		+NT	830 to 880	a	580 to 640	a or w
		+QT	820 to 870	w or o	580 to 640	a or w
X12Ni5	1.5680	+N	800 to 850	a	-	-
		+NT	800 to 850	a	580 to 660	a or w
		+QT	800 to 850	w or o	580 to 660	a or w
X8Ni9 +NT640	1.5662 +NT640	+N plus +NT	880 to 930 + 770 to 830	a	540 to 600	a or w
X8Ni9 +QT640	1.5662 +QT640	+QT	770 to 830	w or o	540 to 600	a or w
X8Ni9 +QT680	1.5662 +QT680	+QT ^c	770 to 830	w or o	540 to 600	a or w
X7Ni9	1.5663	+QT ^c	770 to 830	w or o	540 to 600	a or w
^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa. ^b a: air; o: oil; w: water. ^c See Table 3, footnote c.						

Annex ZA (informative)

Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association to provide a means of conforming to Essential Requirements of the New Approach Directive 97/23/EC.

Once this standard is cited in the Official Journal of the European Union under that Directive and has been implemented as a national standard in at least one Member State, compliance with the clauses of this standard given in Table ZA.1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding Essential Requirements of that Directive and associated EFTA regulations.

Table ZA.1 — Correspondence between this European Standard and the Essential Requirements of EU Directive 97/23/EC, Annex I

Clauses/sub-clauses of this European Standard	Essential Requirements (ERs) of Directive 97/23/EC, Annex I	Qualifying remarks/ Notes
8.4	4.1a	Appropriate material properties
8.2	4.1c	Ageing
8.2 and 8.6	4.1d	Suitable for the processing procedures
9.1	4.3	Documentation

WARNING: Other requirements and other EU Directives may be applicable to the product(s) falling within the scope of this standard.

Bibliography

- [1] EN 10020, *Definition and classification of grades of steel*

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com