

Steel wire and wire products — Steel wire for ropes —

Part 4: Stainless steel wire

The European Standard EN 10264-4:2002 has the status of a British Standard

ICS 77.140.20; 77.140.65

National foreword

This British Standard is the official English language version of EN 10264-4:2002.

The UK participation in its preparation was entrusted to Technical Committee ISE/26, Steel wire, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 30 August 2002

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

EUROPEAN STANDARD

EN 10264-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2002

ICS 77.140.20; 77.140.65

English version

Steel wire and wire products - Steel wire for ropes - Part 4: Stainless steel wire

Fils et produits tréfilés en acier - Fils pour câbles - Partie 4:
Fils tréfilés en acier inoxydable

Stahldraht und Drahterzeugnisse - Stahldraht für Seile -
Teil 4: Draht aus nichtrostendem Stahl

This European Standard was approved by CEN on 4 May 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Designation of product.....	4
4 General conditions of manufacture	4
4.1 Main steel grades and characteristic applications.....	4
4.2 Chemical composition.....	5
4.3 Surface condition.....	6
5 Characteristics and requirements.....	6
5.1 Tensile strength	6
5.2 Diameter tolerances.....	6
5.3 Ductility	7
5.4 Magnetic permeability	7
6 Test methods.....	7
6.1 General.....	7
6.2 Dimension of wire	7
6.3 Tensile test	7
6.4 Reverse bend test	8
6.5 Wrapping test	8
6.6 Tensile test on knotted wire.....	8
6.7 Magnetic permeability	8

Foreword

This document EN 10264-4:2002 has been prepared by Technical Committee ECISS/TC 30 "Steel wires", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2003, and conflicting national standards shall be withdrawn at the latest by February 2003.

This European Standard for wire for ropes is made up of the following parts:

Part 1: General requirements.

Part 2: Cold drawn non alloy steel wire for ropes for general applications.

Part 3: Cold drawn and cold shaped non alloy steel wire for high duty applications.

Part 4: Stainless steel wire.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

EN 10264-4:2002 (E)

1 Scope

This Part of this European Standard specifies the characteristics of stainless steel wire for the manufacture of ropes that are exposed to corrosion and in some cases to a moderate temperature.

This part of this European Standard specifies the following for stainless steel wire for ropes

- dimensional tolerances;
- mechanical characteristics;
- requirements relating to the chemical composition of the stainless steel wire;
- conditions to be satisfied by any coating.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10088-3, *Stainless steels — Part 3: Technical delivery conditions for semi-finished products, bars, rods and sections for general purposes.*

EN 10095, *Heat resisting steels and nickel alloys.*

EN 10218-1, *Steel wire and wire products — General — Part 1: Test methods.*

EN 10264-1, *Steel wire and wire products — Steel wire for ropes — Part 1: General requirements.*

ASTM A342, *Standard test methods for permeability of feebly magnetic materials.*

3 Designation of product

The designation of the product is based on the nominal diameter, chemical composition and minimum tensile strength of the wire.

EXAMPLE Stainless steel wire for rope, diameter 1,5 mm - grade X4CrNi18-12 - strength 1 450 MPa.

Wire for rope EN 10264-4 - 1,5 - X4CrNi18-12 - 1 450

NOTE The grade of steel can be designated numerically, see Table 1.

4 General conditions of manufacture

4.1 Main steel grades and characteristic applications

The grades given in Table 1 are widely used mainly in accordance with EN 10088-3 and EN 10095 with requirements as specified in this part of EN 10264. However, for other specific applications other steel grades specified in EN 10088-3 or EN 10095 may be used with requirements to be agreed between the parties.

Table 1 gives an informative indication of characteristic applications of the mentioned steel grades.

Table 1 — Main steel grades and characteristic applications

Grades of steel		Application
Steel number	Steel name	
1.4301	X5CrNi18-10	for general use in a corrosive environment
1.4310	X10CrNi18-8	as 1.4301 for general use for greater mechanical strength
1.4401	X5CrNiMo17-12-2	for highly corrosive environment particularly in marine atmosphere
1.4303	X4CrNi18-12	for low permeability requirements
1.4841	X15CrNiSi25-21	for ropes also subjected to a moderate temperature

4.2 Chemical composition

In accordance with EN 10088-3 and EN 10095, the chemical composition of the stainless steels shall comply with Table 2.

Table 2 — Chemical analysis in % by mass

Grades of steel		C	Si max.	Mn max.	P max.	S max.	Cr	Mo	Ni	N
Steel number	Steel name									
1.4301	X5CrNi18-10	≤ 0,07	1,00	2,00	0,045	0,015	17,00-19,50		8,00-10,50	≤ 0,11
1.4310	X10CrNi18-8	0,05-0,15	2,00	2,00	0,045	0,015	16,00-19,00	≤ 0,80	6,00-9,50	≤ 0,11
1.4401	X5CrNiMo17-12-2	≤ 0,07	1,00	2,00	0,045	0,015	16,50-18,50	2,00-2,50	10,00-13,00	≤ 0,11
1.4303	X4CrNi18-12	≤ 0,06	1,00	2,00	0,045	0,015	17,00-19,00		11,00-13,00	≤ 0,11
1.4841	X15CrNiSi25-21	≤ 0,20	1,50-2,50	2,00	0,045	0,030	24,00-26,00		19,00-22,00	≤ 0,11

EN 10264-4:2002 (E)**4.3 Surface condition**

Stainless steel wire for ropes shall be supplied either matt (dry drawn) or shiny (surface condition achieved either by polishing or by wet drawing). If a particular appearance is required, it shall be stipulated at the time of enquiry and order.

As an indication, wire of diameter $< 0,50$ mm is normally wet drawn and supplied shiny while wire with a diameter greater than 1,00 mm is commonly dry drawn and supplied matt. For intermediate sizes there is no preference and it will be pending of the manufacturer.

5 Characteristics and requirements**5.1 Tensile strength**

The wire is characterized by a minimum tensile strength. The minimum tensile strength depends on the steel grade and the diameter of the wire. Table 3 specifies the minimum tensile strength for each steel grade. The maximum value shall not exceed the minimum value plus 15 %.

Table 3 — Tensile strength requirements

Nominal diameter d mm	Minimum tensile strength ^a – MPa ^b				
	1.4301 LT ^c	1.4310 NT ^d	1.4303	1.4401	1.4841
$d \leq 0,20$	2 050	2 200	1 600	1 725	1 700
$0,20 \leq d < 0,30$	2 000	2 150	1 575	1 700	1 650
$0,30 \leq d < 0,40$	1 950	2 100	1 550	1 675	1 600
$0,40 \leq d < 0,50$	1 900	2 050	1 550	1 650	1 575
$0,50 \leq d < 0,65$	1 850	2 000	1 525	1 625	1 575
$0,65 \leq d < 0,80$	1 800	1 950	1 525	1 600	1 550
$0,80 \leq d < 1,00$	1 750	1 900	1 500	1 575	1 550
$1,00 \leq d < 1,25$	1 700	1 850	1 475	1 550	1 525
$1,25 \leq d < 1,50$	1 650	1 800	1 450	1 500	1 500
$1,50 \leq d < 1,75$	1 600	1 750	1 425	1 450	1 475
$1,75 \leq d < 2,00$	1 550	1 700	1 400	1 400	1 450
$2,00 \leq d < 2,50$	1 500	1 650	1 350	1 350	1 400
$2,50 \leq d \leq 3,00$	1 450	1 600	1 300	1 300	1 350

^a For ropes for specific applications, lower strengths may be requested.
^b 1 MPa = 1 N/mm².
^c Low level of tensile strength.
^d Normal level of tensile strength.

5.2 Diameter tolerances

The diameter measured shall comply with the tolerances specified in Table 4. The out of roundness shall not be greater than half the tolerance on diameter.

Table 4 — Diameter tolerances

Dimensions in millimetres

Nominal diameter d	Tolerance ($\pm$)
$0,12 \leq d < 0,22$	0,006
$0,22 \leq d < 0,37$	0,008
$0,37 \leq d < 0,65$	0,010
$0,65 \leq d < 1,01$	0,015
$1,01 \leq d < 1,78$	0,020
$1,78 \leq d < 2,78$	0,025
$2,78 \leq d \leq 3,00$	0,030

5.3 Ductility

Because of the specific nature of this material and its deformation structure (by drawing), conventional ductility tests show a wide spread. When they are required, the following ductility tests shall be carried out: reverse bending test, tensile strength test on knotted wire or wrapping test. The parties shall agree upon the required ductility tests and on the minimum required results.

5.4 Magnetic permeability

When the grade X4CrNi18-12 (1.4303) is required with a very low permeability (non-magnetic), the magnetic permeability shall be less than 1,05.

The grade X4CrNiMo17-12-2 (1.4401) may also be requested with low permeability. In this case, the requirements shall be agreed between the parties.

6 Test methods

6.1 General

Tests shall be carried out in accordance with EN 10218-1 and EN 10264-1 with the following observations.

6.2 Dimension of wire

The diameter of the wire shall be measured with a micrometer with an accuracy of at least 0,001 mm for dimensions below 0,65 mm. For larger wire, an accuracy of 0,01 mm is acceptable.

6.3 Tensile test

The tensile test shall be carried out in accordance with EN 10264-1.

EN 10264-4:2002 (E)**6.4 Reverse bend test**

The reverse bend test shall be carried out in accordance with EN 10218-1.

6.5 Wrapping test

When coiled for 8 turns around a mandrel of equal diameter to the wire, the wire shall show no signs of breaking; the test shall be carried out in accordance with EN 10218-1.

6.6 Tensile test on knotted wire

For diameters < 0,50 mm, the tensile test on knotted wire shall be carried out in accordance with EN 10218-1. The strength is then measured on a wire in which 1 simple knot has been made. This strength is expressed as a percentage of the tensile strength of the unknotted wire.

6.7 Magnetic permeability

Magnetic permeability shall be measured in accordance with ASTM A342 method 4 in a field of 500 to 1 000 Oersted.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.